MICROCOPY RESOLUTION TEST CHART

NATIONAL BUREAU OF STANDARDS-1963-A

NBSIR 85-3282

SURVEY OF ALTERNATE STORED CHEMICAL ENERGY REACTIONS

L. P. Cook
E. R. Plante

U.S. DEPARTMENT OF COMMERCE
National Bureau of Standards
Institute for Materials Science and Engineering
Ceramics Division
Gaithersburg, MD 20899

December 1985

Prepared for:
Department of the Navy
Office of Naval Research
Arlington, VA 22217

U.S. DEPARTMENT OF COMMERCE, Malcolm Baldrige, *Secretary*

NATIONAL BUREAU OF STANDARDS, Ernest Ambler, *Director*

Annual Report

For the Period May 25, 1984   May 25, 1985

L. P. Cook and E. R. Plante

Inorganic Materials Division
Institute for Materials Science and Engineering
National Bureau of Standards
Gaithersburg, MD   20899

September 15, 1985

Survey of Alternate Stored Chemical Energy Reactions

Table of Contents

Abstract

A survey of eight alternative liquid metal stored chemical energy reactions has been made for purposes of comparison with the lithium-aluminum/water, lithium/sulfur hexafluoride, and other reaction schemes. The objective of the study was to survey the potential of these eight reactions as alternate stored chemical energy systems and to develop priorities for future study. Experimental data on the products of reaction and kinetics of reaction are presented for: Li/H_2O; H_2/O_2), $(Li/H_2O; NaO_2/H_2O; H_2/O_2)$, $(MgAl/H_2O; H_2/O_2)$, and $LiAl/ClO_3F)$. These data have been collected using thermogravimetry and Knudsen effusion mass spectrometry, with x-ray diffraction analysis of experimental products. Among other results, the data show that the aluminum component of the fuels is relatively inert to oxidation up to 650 °C. Above this temperature, materials limitations have hampered the collection of experimental data.

Thermodynamic analysis has been used to extend the data on each of the eight reaction schemes, and to predict the chemical reaction which best represents the complete oxidation of each fuel by the indicated oxidant at 1100 K. Enthalpies have been calculated for each fuel/oxidant combination. Safety considerations are also discussed for each. Suggestions for future research are given, including suggestions for overcoming the materials problems encountered in this study.

I. Introduction

Recently there has been much interest in the use of light metals as fuel for stored chemical energy devices. A system currently in usage involves molten lithium metal and sulfur hexafluoride, according to the reaction,

$$8Li + SF_6 \rightarrow Li_2S + 6LiF \qquad [1]$$

Under development (1) is a system using lithium aluminum alloy as the fuel and water as the oxidant, according to the reaction:

$$LiAl + 2H_2O \rightarrow LiAlO_2 + 2H_2 \qquad [2a]$$

The hydrogen liberated is combined with oxygen to yield water:

$$2H_2 + O_2 \rightarrow H_2O \qquad [2b]$$

The water produced in this way is returned to [2a] to complete the cycle. In our laboratories investigation is continuing of reaction [2a], which is potentially much more complex than as written (2).

In addition to reaction [2], there are other possible alternate systems of interest and it is desirable to make a preliminary survey of these, to determine if certain ones might emerge as clear choices for further development, or at the least, if others might be eliminated from further consideration. The fuel/oxidant combinations that have been suggested are:

$$\text{Li/H}_2\text{O; H}_2\text{/O}_2 \qquad\qquad\qquad [3]$$

$$\text{Li/H}_2\text{O; NaO}_2\text{/H}_2\text{O; H}_2\text{/O}_2 \qquad\qquad [4]$$

$$\text{MgAl/H}_2\text{O; H}_2\text{/O}_2 \qquad\qquad\qquad [5]$$

$$\text{LiAl/ClO}_3\text{F} \qquad\qquad\qquad\qquad [6]$$

$$\text{LiAlMg/ClO}_3\text{F} \qquad\qquad\qquad\qquad [7]$$

$$\text{LiBe/ClO}_3\text{F} \qquad\qquad\qquad\qquad [8]$$

$$\text{Li/C}_{11}\text{F}_{20} \qquad\qquad\qquad\qquad [9]$$

$$\text{LiB/NF}_3 \qquad\qquad\qquad\qquad [10]$$

Combinations [3], [4], and [5] utilize a final stage of combustion in which hydrogen is burned, in a reaction identical to reaction [2b] above. Combinations [6] through [10], however, are envisioned as largely single-stage energy release schemes. To fully evaluate all these candidates it is desirable to have the following basic information:

(a) identity of the products of fuel/oxidant reaction

(b) an indication of the kinetics, especially the minimum temperature required for spontaneous combustion and self-sustaining reaction

(c) an estimate of the enthalpy of reaction

(d) knowledge of toxicity of reaction products

Information collected to date for each of the fuel/oxidant combinations is summarized in the paragraphs that follow. Most experiments were com-

pleted using a Mettler[1] thermoanalysis system, except for reaction [6],
which was also investigated mass spectrometrically. Following a presenta-
tion of data for each of the above reaction schemes, a general discussion
and recommendations for follow-up research are given. Results of a
literature search are given in an Appendix (Section XIII).

II. Li/H_2O; H_2/O_2

A. Starting Materials and Container Materials

The starting material used for these experiments was finely powdered
lithium metal (-140 mesh, 99.95% pure on a metal basis). This material
had some surface oxidation upon receipt from the vendor, causing it to
have a slightly grayish cast; the contaminants were tentatively identified
as lithium carbide (Li_2C_2), lithium hydride, and lithium hydroxide, on
the basis of weak x-ray diffraction peaks. All materials handling
operations involving the lithium metal were completed in a glove box.

Quantitative study of the oxidation of metallic lithium poses
special materials problems. Any container must be capable of withstand-
ing attack by both metallic lithium and the oxidant. Silica glass is
not a suitable container in the presence of both the lithium fuel and
the water oxidant. Graphite and molybdenum are mentioned in the litera-
ture (3, 4) as container materials for lithium alloys; however both are
attacked by oxidants at relatively low temperatures. A nickel-based
alloy would appear to offer promise; however, nickel could

---

[1]Certain commercial equipment, instruments, or materials are identified
in this paper in order to adequately specify the experimental procedure.
Such identification does not imply recommendation or endorsement by the
National Bureau of Standards, nor does it imply that the materials or
equipment identified are necessarily the best available for the purpose.

be expected to undergo a certain degree of oxidation even at relatively low temperatures, affecting the results of sensitive thermogravimetric experiments, and possibly contaminating the sample. BN is a possible material, but experiments with LiAl (see below) suggest lithium abosrption. Perhaps the strongest candidate crucible materials for future work are BeO (5) and MgO; however, as these were not available, all measurements to date were completed using readily available alumina crucibles at temperatures below the melting point of lithium metal.

B. Reaction Products

Lithium metal was reacted with water-saturated flowing argon (30,000 ppm H_2O) in the thermoanalyzer. At 25 °C, slow reaction of lithium metal with water produces $LiOH.H_2O$. However the reaction probably proceeds sequentially, starting with LiOH, as evidenced by x-ray analysis of samples from different zones within the reaction cell. Near the bottom of the cell, products were largely LiOH; near the top, the hydrate was dominant. At 100 °C, the reaction product is almost entirely LiOH; small amounts of the hydrate are believed to have formed as the experiment cooled.

C. Kinetics

The finely powdered lithium metal used in these expeiments is highly reactive at room temperature in spite of the thin surface coating. This is evidenced by rapid reaction when deliberately exposed to the atmosphere. When placed in contact with water, violent reaction ensues, and explosion occurs due to spontaneous ignition of the evolved hydrogen.

In the thermoanalyzer experiments, the reaction was purposefully set up to proceed in controlled fashion. Reaction curves at 25 and 100 °C are shown in Fig. 1. The 25 °C curve shows a nearly linear segment from 0 to 1500 min. of reaction time, implying that reaction control in the early stages is not associated with build-up of a product layer, but rather may be linked to the rate of supply of the water vapor. The second half of the 25 °C curve is nonlinear. This could be due to the influence of the product layer of LiOH.H_2O, but is more likely to be due to the increased diffusion path required for vapor to reach the powders in the bottom of the cell. The reaction was stopped prior to completion. Theoretically completion would have occurred at a fractional weight gain of 5.1 (compared with 3.7 at the termination of the experiment). This number assumes complete conversion to Li(OH).H_2O.

By contrast, at 100 °C, the entire curve appears to be nonlinear. This suggests influence of the product layer (in this case LiOH). The reaction appears to have terminated in spite of the fact that the theoretical fractional weight gain of 2.5 was not reached. This probably indicates that the surface contamination of the Li powdered starting material is more severe than the x-ray analysis suggested. Future experiments will employ a much more nearly pure lithium powder.

D. Enthalpy

Thermodynamic data for calculation of the enthalpy of oxidation of molten lithium metal by H_2O are available in the JANAF tables (6). Enthalpy production in kcal per gram of fuel plus oxidant can be calculated, if the lithium oxidation reaction is combined with burning of the evolved hydrogen and recycling of water thus produced:

$$Li + H_2O \rightarrow LiOH + (1/2)H_2 \qquad\qquad [11]$$

$$(1/2)H_2 + (1/4)O_2 \rightarrow (1/2)H_2O \qquad\qquad [12]$$

$$Li + (1/2)H_2O + (1/4)O_2 \rightarrow LiOH \text{ (combined reaction)} \qquad [13]$$

The calculated value[2] at 1100 K (827 °C) is 3.5 kcal/g. If LiOH did not form, the combined reaction would be:

$$2Li + (1/2)O_2 \rightarrow Li_2O \qquad\qquad [14]$$

for which the enthalpy yield is 4.8 kcal/g. Clearly there is a heavy energy penalty paid by loss of hydrogen in the cycle to form LiOH.

E. Safety Considerations (7)

Lithium metal reacts exothermically with the moisture in human tissue, causing both thermal and chemical burns. An explosion hazard exists when the metal is exposed to moisture of any form, or to any other oxidizing material. When heated in air or burned it emits toxic fumes of Li_2O and LiOH. It reacts with nitrogen at high temperatures.

III. Li/H_2O; NaO_2/H_2O; H_2/O_2

A. Starting Materials

The Li/H_2O part of the reaction scheme has been discussed above. The role of NaO_2 is to provide oxygen for the second stage burning of hydrogen.

---

[2] All energy yield calculations in this report are listed in terms of kcal per gram of fuel plus oxidant.

The NaO_2 used in these experiments was indicated by the vendor to be 95% NaO_2. X-ray powder diffraction analysis of the starting material which consisted of pale yellow granules, yielded a very complex pattern containing peaks for NaOH, NaO_2(I) and several unidentified peaks.

B. Reaction Products

NaO_2 was placed in a platinum cell in the thermoanalyzer. The sample was brought to temperature (25 or 100 °C) and then a stream of flowing water-saturated argon (30,000 ppm H_2O) was introduced. At the conclusion of the 100 °C experiment the sample was x-rayed. This was not possible for the 25 °C experiment, which produced liquid; apparently the NaO_2 (or the NaOH produced from it) is deliquescent at 25 °C. The 100 °C experiment yielded predominantly NaOH; the lesser amount of $NaOH.H_2O$ present is thought to have formed as the experiment cooled.

C. Kinetics

Reaction curves for NaO_2/H_2O at 25 and 100 °C are shown in Fig. 2. The 25 °C curve consists of two linear weight gain portions. Interestingly the slope increases for the later segment. This is interpreted as follows. During the early 25 °C segment, the reaction involves loss of oxygen and gain of water:

$$2NaO_2 + 3H_2O \rightarrow 2(NaOH.H_2O) + (3/2)O_2 \qquad [15]$$

The theoretical fractional weight gain for this reaction is 0.06, which is near the change in slope for the 25 °C curve. During the later segment of the 25 °C reaction curve in Fig. 2, the product is thought to be the deliquescent liquid observed at the conclusion of the experiment, produced according to the reaction:

$$NaOH \cdot H_2O + H_2O \rightarrow (NaOH, H_2O) \ (\ell) \qquad [16]$$

Possibly formation of the liquid results in increased accessibility by the gas, explaining the increased slope.

At 100 °C, the reaction of NaO_2 with water vapor produces a nearly linear weight loss as would be expected from the reaction:

$$2NaO_2 + H_2O \rightarrow 2NaOH + (3/2)O_2 \qquad [17]$$

This reaction would yield a theoretical weight loss of 0.27. The 100 °C reaction apparently terminates at less than this value, reflecting the presence of the NaOH impurity noted in the x-ray analysis of the starting materials.

D. Enthalpy

If the sodium superoxide reaction is combined with the lithium/water oxidization reactions, we have the following:

$$(1/3)NaO_2 + (1/6)H_2O \rightarrow (1/3)NaOH + (1/4)O_2 \qquad [18]$$

$$Li + (1/2)H_2O + (1/4)O_2 \rightarrow LiOH \qquad [19]$$

$$(1/3)NaO_2 + (2/3)H_2O + Li \rightarrow (1/3)NaOH + LiOH \qquad [20]$$

(combined reaction)

An enthalpy of formation for NaO_2 at 298 K can be estimated as -62.7 kcal.

Neglecting the heat required to bring the oxygen from the first stage up to 1100 K, the total energy release in reaction [20] is -2.2 kcal/g. This is significantly less than the -3.5 kcal/g calculated earlier for the Li/H_2O; H_2/O_2 combination. However it may be that there are advantages associated with use of a solid as the oxidant source rather than a compressed gas.

E. Safety Considerations (7)

Hazards associated with lithium are noted in the discussion of Li/H_2O above. Sodium superoxide has much the same toxicity as NaOH, which it forms upon contact with moisture. Contact with skin could be expected to cause burns and ulceration; inhalation of the mist or powder could cause damage to the upper respiratory tract and lungs. Heating could cause violent decomposition. Contact with moisture or reducing agents could result in explosion.

IV. $MgAl/H_2O$; H_2/O_2

A. Starting Materials

Magnesium aluminum alloy of 50/50 atomic ratio was prepared in the NBS metals processing lab by melting high purity magnesium and aluminum together under a halide flux and casting the melt into a steel chill mold. The resulting ingot was very brittle and was easily crushed in a mortar and pestle in a glove box. A (-200, +400) sieve fraction was then prepared for the experiment and stored in the glove box until use. An x-ray diffraction pattern showed characteristic peaks for Al_2Mg_3 with a few additional unidentified peaks of low intensity.

B. Reaction Products

The powdered alloy was placed in an alumina cell in a glove gox and transferred to the thermoanalyzer system. Next the specimen was brought to 650 °C in an argon atmosphere. At this temperature the specimen was completely melted, according to the Mg-Al phase diagram (8). Next, argon saturated with water at 25 °C (30,000 ppm H_2O) was flowed continuously over the sample. At the conclusion of reaction the gray, porous sample was cooled, removed and x-rayed. The x-ray powder pattern showed strong peaks for aluminum metal and MgO (periclase). Apparently only the magnesium component of the molten alloy was oxidized, as there were no peaks for Al_2O_3, $MgAl_2O_4$ or any other aluminous phases.

C. Kinetics

Rate data for the oxidation of molten MgAl by water vapor are shown in Fig. 3. The meaning of the step in the weight gain curve at about 100 minutes of reaction time is not clear. However the two segments of this curve on either side of the break have substantially linear portions, suggesting that diffusion through a product layer of increasing thickness is not a controlling factor during most of the reaction. The reaction appears to slow to a very low rate as the fraction reacted approaches 0.30. This is in agreement with the x-ray analysis, which indicates essentially all the Mg has been oxidized; complete oxidation of the Mg to periclase would correspond to a fractional weight gain of 0.31, very close to that observed; on the other hand, complete oxidation of both the magnesium and the aluminum would result in a fractional weight gain of 0.62.

D. Enthalpy

Referring to the system Mg-Al-O-H, at least three possible oxidation reactions involving the 1:1 alloy and water could occurr. These are

summarized below:

$$2MgAl + 5H_2O \rightarrow MgO + MgAl_2O_4 + 5H_2 \qquad [21a]$$

$$5H_2 + (5/2)O_2 \rightarrow 5H_2O \qquad [21b]$$

$$2MgAl + 5H_2O \rightarrow 2MgO + Al_2O_3 + 5H_2 \qquad [22a]$$

$$5H_2 + (5/2)O_2 \rightarrow 5H_2O \qquad [22b]$$

$$MgAl + H_2O \rightarrow MgO + Al + H_2 \qquad [23a]$$

$$H_2O + (1/2)O_2 \rightarrow H_2O \qquad [23b]$$

To complete enthalpy calculations for these reactions an estimate for the enthalpy of formation of molten MgAl was made using the ideal solution approximation. Calculated enthalpy release values for the three reaction pairs are respectively, -3.8, -3.8, and -2.2 kcal/g. Clearly, formation of spinel (reaction [21a] vs. reaction [22a]) affects the energy yield very little. Reaction [23a] has been included because it is the one observed, and clearly its occurrence instead of [21a] or [22a] results in substantially lower energy yield. Presumably at some higher temperature the aluminum component will begin to react according to reaction [21a] or [22a].

E. Safety Considerations (7)

Hazards data are not available for MgAl alloy. Aluminum is not regarded as a poison, although inhalation of finely divided powders can damage the lungs. Magnesium on the other hand can cause chemical gas

gangrene if it enters the body, due to generation of hydrogen. Fine
magnesium powder readily ignites by exposure to spark or flame.

V. $LiAl/ClO_3F$

A. Starting Materials

The starting material for these experiments was powdered LiAl.
The material as received was packed under argon and visually showed no
signs of surface contamination--all surfaces were bright and shiny.
X-ray analysis showed only peaks of LiAl. All manipulations involving
this material were done in a glove gox through which a continuously
purified argon atmosphere was recirculated. The material used in these
experiments was a (-200, +400) sieve fraction. Transfer to the thermo-
analyzer was accomplished in a glove bag, flushed repeatedly with purified
argon.

The ClO_3F (perchloryl fluoride) was obtained from the vendor in
cylinders containing either 100 g or 250 g. Principal impurities were
N_2, O_2, CO_2, H_2O and HF (see section on mass spectrometry).

Gas was run through a corrosive gas regulator and then through a
column containing NaOH pellets and molecular sieve, and finally through
a flowmeter and then into the thermoanalyzer. The ClO_3F, a very dense
gas, was piped directly into the crucibles in the thermoanalyzer exper-
iments. Provision was made for mixing the ClO_3F with continuously var-
iable amounts of argon. However, all thermoanalyzer experiments reported
were carried out using a flow of pure ClO_3F since it was discovered that
the reactions proceeded in controlled fashion so that no argon dilution
was necessary. Although argon was used to flush the balance components

during the experiments, it is estimated that the effective partial
pressure of ClO_3F over the specimens during these experiments was close
to 1 atmosphere.

B. Reaction Products

Initially, experiments were conducted in alumina crucibles; however
these were unsatisfactory above 700 °C, owing to the corrosiveness of the
molten alloy. Crucibles of $LiAlO_2$ have been fabricated and these appear
to offer promise for application in higher temperature experiments.
Additionally MgO and BeO offer promise. Boron nitride crucibles were
fabricated and tested in contact with LiAl at 800 °C. They seem to hold
up to attack by the molten alloy well, except for a slight discoloration,
which may be associated with diffusion of Li. Also a steady and extensive
weight gain of the crucible occurred during preliminary tests under an
atmosphere of purified argon. As we have no explanation for or solution
to this problem, use of the BN crucibles was discontinued. Calcia-
stabilized zirconia and silica glass crucibles were employed for the
mass spectrometric studies, with mixed results. All other experiments
reported employed alumina crucibles.

At the conclusion of the $LiAl/ClO_3F$ experiments, crucibles were
removed and placed in an inert atmosphere. X-ray mounts were prepared
in the glove box and x-rayed under flowing N_2. Results of x-ray analysis
are indicated in Table 1, below.

As can be seen from Table 1, experimental results vary greatly
depending upon experimental conditions. The following generalizations
can be made, however, for the range of conditions investigated (350-
650 °C, $P_{ClO_3F} = 1$ atm; or, 900 °C, $P_{ClO_3F} = 10^{-5}$ atm).

(1) Fluorides (Li_3AlF_6, AlF_3, LiF) appear to be by far the dominant reaction products.

(2) Chlorides may form during initial stages of oxidation[3] (see discussion of kinetics) but are relatively minor phases in the end products.

(3) The lithium in the alloy is preferentially oxidized leaving behind aluminum which behaves as though inert (see also discussion of MgAl oxidation).

(4) The occurrence of oxides as oxidation products is limited in these experiments to low partial pressures of ClO_3F and/or high temperatures.

C. Mass Spectrometry

   i) Outline of Method

In this technique, the Li-Al alloy contained in a Knudsen cell is exposed to ClO_3F introduced into the cell through a gas inlet system. At appropriate temperatures, reaction products undergo vaporization into the source of the mass spectrometer where the gaseous products are ionized and mass analyzed. The major advantage of this method is that it can in principle detect gaseous reaction products. A second advantage is that the number of collisions of reactant vapor with the condensed phase may be controlled at a low value so that the kinetics of the process can be substantially solved.

In the present measurements, however, it was found that reaction rates are quite slow even up to temperatures as high as 1000 °C so that modifications in the experimental arrangement to enhance reaction rates will be advantageous.

---

[3] Oxidation is here used in the generic chemical sense.

ii) Vaporization Considerations

At low temperatures some of the reaction products may be relatively non-volatile so that they will not be detected by mass spectrometric analysis. On the basis of data in the literature, the metal chlorides are more volatile than the metal fluorides while the metal oxides are non-volatile up to temperatures of 1000 °C or so. Also, because the halides will form a salt solution, complexing to form interhalide compounds may influence the volatity of the solution. For example, formation of LiAlCl$_4$ would greatly reduce the pressure expected from formation of AlCl$_3$.

iii) Experimental set-up

These measurements were made using a fused silica effusion sampler. The Li-Al alloy was contained in a calcia-stabilized zirconia cup supported within the effusion sampler. The ClO$_3$F was delivered to the gas inlet tube through a small leak valve. The Li-Al alloy was loaded into the zirconia cell in a dry-box then transferred to the mass spectrometer under argon to reduce the reaction of the Li-Al alloy with ambient water vapor.

An effusion orifice of 1 mm diameter was used in the effusion sampler. This proved to be too large as the ClO$_3$F reacted much less rapidly with the Li-Al alloy than expected.

The control valve was attached to the ClO$_3$F cylinder in the dry box so the ClO$_3$F was diluted with Ar during the earlier parts of the experiment.

iv) Analysis of ClO$_3$F

Mass spectrometric sampling of the commercial ClO$_3$F gas showed predominant peaks at m/e values of 104, 102, 85, 83, 69, 67, 53, and 51 corresponding to the ^{37}Cl and ^{35}Cl isotopes of the species ClO$_3$F$^+$,

ClO_3^+, ClO_2^+, and ClO^+. Except for ClO_3F^+, these peaks are due to fragmentation of the ClO_3F during the ionization process using electrons at 30v. Besides the ClO_3F, Ar which was introduced from the dry box installation of the regulator was also observed. By comparing the mass spectrum with the ClO_3F gas flow on or off, it was determined that the ClO_3F also contained a small amount (perhaps a percent or so) of air (N_2, O_2, CO_2, and H_2O). The H_2O had apparently partially reacted with the steel cylinder and produced slight traces of HF (mass 20), $H^{35}Cl$ (36), and $H^{37}Cl$ (38). However, it is not likely that the contamination had significant effect on the reaction of ClO_3F with the alloy.

v) Reaction of Li-Al Alloy with ClO_3F

The first mass peaks due to reaction of ClO_3F with the Li-Al alloy were observed at 420 °C. These peaks were Li^+ from fragmentation of LiCl(g), $LiCl^+$ from ionization of the LiCl(g) and Li_2Cl^+, from ionization of the Li_2Cl_2(g) parent.

One might expect Al-Cl species in this temperature range but none were observed, in spite of the fact that loss of volatile substances is indicated by the analogous thermogravimetric experiment. It is clear from the presence of both LiCl(g) and Li_2Cl_2(g) that a condensed halide phase was formed on the sampler.

With time, the ratio of $LiCl^+$/Li_2Cl^+ gradually increased. This probably showed that LiF was also forming in the condensed phase and reducing the activity of LiCl. At 600 °C, Li_2F^+ from the fragmentation of Li_2F_2 was observed in the mass spectrum. Over the temperature range from 600-900 °C ions corresponding to parent molecules LiCl, Li_2Cl_2, LiF, and Li_2F_2 were observed. It did not appear that any Al bearing species were formed in the gas phase.

At the conclusion of the experiment, the Li-Al alloy still had a powdery appearance even through it had been heated several hundred degrees above the melting point.

An x-ray diffraction pattern of the residue revealed the presence of $LiAlO_2$ with perhaps an equal amount of unreacted Al (see Table 1).

vi) $Al-ClO_3F$ Interaction

Because Al bearing species were not observed from the Li-Al alloy, a mass spectrometric experiment was carried out using only powdered Al in the effusion cell. The purpose of this experiment was to see if it was possible to form Al bearing species by reactions with ClO_3F. Near 500 °C species corresponding to the halide ions AlF^+, $AlCl^+$, AlF_2^+, $AlClF^+$, Al_3^+, AlF_2Cl^+, $AlCl_2F^+$, and $AlCl_3^+$ were observed. Because of the number of complex species in the vapor phase, the existence of a condensed phase at this temperature consisting of mainly AlF_3 seems likely. The duration of the experiment during which Al-halide species was generated was quite short. All of the Al bearing species decreased with time and increasing the ClO_3F flow rate and the temperature had no effect on increasing their intensity. This seems to indicate that the chlorination and fluoridation processes took place at only selected sites in the Al powder which were gradually depleted or lost, perhaps because of oxidation.

At 760 °C, most of the Al halide peaks had vanished except for AlF_2^+ which is a major fragmentation product of $AlF_3(g)$. The experiment was terminated after a brief heating period at 800 °C. Visual examination of the residue at the conclusion of the experiment revealed that most of the sample still had a powdery texture but a few small spheres resulting from melting the sample were also present. Since the sample

was heated to about 150 °C above the melting point of Al, the powdery

texture of the sample must result from an oxide skeleton on the outside

surface of each grain in the powder. The sample initially weighed

118 mg and gained 2.2 mg during the experiment, despite loss of the

halides, indicating that a small amount of oxidation took place.

D. Kinetics

Thermogravimetric rate data for the reaction of LiAl with ClO_3F are

shown in Fig. 4 at temperatures of 350, 450, 550 and 650 °C. It is

presumed on the basis of the Li-Al phase diagram (9) that the LiAl was

solid during these experiments. With the exception of the 350 °C ex-

periment, rate curves all initially show a rapid weight gain at a nearly

steady rate. This continues until a weight fraction gain of between 0.5

and 0.7 has been reached. At this point the rate of weight gain decreases

for a short time and then increases again. This behavior is especially

pronounced in the 650 °C experiment, where a small weight loss with time

is apparent, followed by an increase in the rate of weight gain. This

weight loss (and possibly, as well, the temporary decrease in rate of

gain at all four temperatures) is best interpreted as due to formation

of a volatile reaction product, most probably $AlCl_3$. Continued reaction

leads to a similar ultimate weight gain of between 0.9 and 1.1 for

experiments at all four temperatures, 350, 450, 550 and 560 °C (see

Table 1). This is true in spite of the fact that the products are

somewhat different in each case. Table 2 lists hypothetical reactions

of LiAl with Cl, O and F and combinations thereof, together with theo-

retical weight gains. These reactions have been derived with the aid of

thermodynamically calculated equilibrium phase compatibilities shown in

Fig. 7. Calculated weight gains are highly variable, but the partial

fluorination reactions [26] and [27] of Table 2 best approximate the

experimental products observed (Table 1). The fractional weight gains calculated for these reactions are 0.56 and 1.12, respectively, encompassing the range observed.

It seems likely from the curves in Fig. 4 that more than one reaction has occurred during the oxidation of LiAl by ClO_3F. It also seems likely that early stage condensed phase products undergo subsequent reaction with time to yield a new generation of products. In future experiments, reacion of LiAl with ClO_3F will be completed at higher temperatures, where hopefully a rapid approach to equilibrium will eliminate many of these complications. It is hoped that mass spectrometer measurements will be carried out at higher pressures of ClO_3F using a transpiration system.

E. Enthalpy

From Table 1 it can be seen that the reaction products at temperatures of 650 °C and below differ greatly, depending upon temperature. Further, oxidation of the alloy is far from complete, and the majority of the aluminum component of the alloy appears to have remained in the metallic state. The reaction products suggest disequilibrium among themselves; for example, Li_3AlF_6, AlF_3 and LiF are not in stable equilibrium together. The principal difficulty then is in extrapolating these limited results to a higher temperature such as 1100 K, at which oxidation could be expected to be much more complete, so that a meaningful enthalpy yield calculation can be done.

The LiAl/ClO_3F reaction can be described by the five component chemical system Li-Al-Cl-O-F. Fortunately thermodynamic data are available for many of the end-member compounds in this system and so a preliminary thermodynamic analysis can be completed. This results in an

estimated equilibrium reaction for complete oxidation which can be used
to calculate enthalpy yield. The thermodynamic analysis was completed
as follows. Fig. 5 depicts graphically the compositional regions of
interest in the three principal quaternary subsystems contained within
the five component system. Fig. 6 shows calculated phase compatibilities
for important ternary reciprocal systems in Fig. 5. These compatibilities
are schematic and indicate major features of phase equilibria which are
consistent with known thermodynamic data, according to the reactions in
Table 3. On the basis of Fig. 6, Fig. 7 has been constructed. This
shows calculated equilibrium relations at 1100 K for the phase regions
shown in Fig. 5. Based on Fig. 6 and 7, Fig. 8 has been constructed,
showing calculated equilibrium relations at 1100 K among phases most
likely to form as products of complete reaction of LiAl and ClO_3F. The
reaction suggested by Fig. 8 is:

$$2LiAl + ClO_3F \rightarrow Al_2O_3 + LiF + LiCl \qquad [74x]$$

It should be emphasized that there is no direct experimental evidence
yet in support of this reaction: however on purely thermodynamic grounds
it is the favored reaction. To complete the enthalpy calculation, data
for LiAl were estimated using the ideal solution approximation. The
resulting value of enthalpy yield for this reaction is 3.8 kcal/g.

F. Safety Considerations (7)

Safety hazards associated with LiAl are similar to those associated
with Li as noted above, although reaction with moisture is considerably
less vigorous at room temperature. Perchloryl fluoride is a highly
toxic gas which causes symptoms of asphyxiation and poisoning similar to

CO, although recovery is said to be rapid provided exposure has not been prolonged. The gas has a sweet odor, but this cannot be relied upon to indicate toxic concentrations. Perchloryl fluoride is readily absorbed through the skin. Although nonflammable, it does support combustion, as it is a powerful oxidizer. When heated to decomposition, it emits highly toxic fumes of chlorides and fluorides.

VI. LiAlMg/ClO$_3$F

A. Enthalpy

At the time of writing, experiments have not yet been completed in this system, owing to lack of available starting material. Therefore enthalpy yield estimates must be made solely on the basis of preliminary thermodynamic analysis. The fuel/oxidant reaction is represented by the 6-component system Li-Al-Mg-Cl-O-F. The phase equilibrium topology is of course impossible to represent in three dimensions; nonetheless, progress can be made by consideration of the six quaternary reciprocal systems shown in Fig. 9. By calculation of the reactions in Table 4, the schematic ternary phase compatibilities shown in Fig. 10 have been derived. From additional reactions in Table 4 and compatibilities in Fig. 10, construction of Figs. 11 and 12 was made possible. Fig. 11 pertains to progressive chlorination, fluorination or oxygenation of fuel. Fig. 12 relates to the equilibrium products of complete reaction. Table 5 gives some postulated equilibrium reactions involving progressive reaction of LiAlMg fuel with Cl, F, O and combinations thereof.

Based on the above considerations, the following is thought to represent complete reaction of LiAlMg alloy (1:1:1 atomic) with ClO$_3$F:

$$4LiAlMg + 3ClO_3F \rightarrow MgF_2 + LiF + 3LiCl + 2MgAl_2O_4 + MgO \qquad [134]$$

The calculated enthalpy yield for this reaction at 1100 K is 3.6 kcal/g.

B. Safety Considerations (7)

Safety hazards are similar to those noted for $LiAlMg/ClO_3F$ above.

VII. $LiBe/ClO_3F$

A. Enthalpy

Because of the toxicity of beryllium and beryllium compounds, ex-
periments have not been conducted on the oxidation of lithium-beryllium
alloy by ClO_3F. Hence any estimate of enthalpy release must rely soley
upon thermodynamic estimates of the actual reaction. A thermodynamic
analysis of the five component system Li-Be-Cl-O-F was completed as
follows. Fig. 13 shows the three quaternary subsystems of interest.
Based on reactions in Table 6, the ternary phase compatibilities in
Fig. 14 have been constructed. Based on these compatibilities and
additional reactions in Table 6, the schematic quaternary phase com-
patibilities in Fig. 15 have been derived; these show the results of
progressive chlorination, fluorination, or oxygenation of LiBe fuel
(Table 7 lists equilibrium reactions involving LiBe fuel with various
combinations of Cl, O and F). Fig. 16 indicates calculated compati-
bilities among likely reaction products. The reaction postulated on the
basis of thermodynamic data for complete oxidation of LiBe by PCF is:

$$8LiBe + 3ClO_3F \rightarrow 8BeO + Li_2O + 3LiF + 3LiCl \qquad [169]$$

The enthalpy relased by this reaction at 1100 K would be 4.6 kcal/g.

B. Safety Considerations (7)

Lithium and beryllium do not form stable intermetallic compounds together (10) and would be expected to be present together in fuel as the chemically uncombined metals. For a discussion of Li safety hazards, see Li/H_2O above. Beryllium is highly toxic both in metallic form and in compound form. Many of the beryllium salts have high vapor pressures, especially when heated. Symptoms of exposure usually involve respiratory distress of varying severity; symptoms may be delayed for several years after exposure. Chronic berylliosis can lead to death from respiratory and cardiac failure. In addition to harm incurred by inhalation, beryllium and its compounds also act on the skin, causing lesions and tumors. Beryllium by itself does not present an explosion hazard, however the admixed lithium in the fuel obviously does. For a discussion of perchloryl fluoride safety refer to LiAl/ClO_3F above.

VIII. Li/$C_{11}F_{20}$

A. Starting Materials

The fluorocarbon compound $C_{11}F_{20}$ was not obtainable from commercial suppliers; the closest molecular weight compound available was the structurally similar double ring compound $C_{11}F_{19}$, an apparently stable, clear liquid. Experiments have not yet been completed due to the necessity of installing a special furnace with a boiling chamber for the liquid oxidant on the thermoanalyzer. It is hoped that loan from another facility of a water vapor furnace (which would also provide 1 atm of P_{H_2O} for the Li/H_2O and MgAl/H_2O experiments) will provide a solution to this experimental problem.

B. <u>Enthalpy</u>

In the absence of experimental data, it is again necessary to utilize thermodynamic estimates in arriving at an oxidation reaction for the enthalpy calculation. The system Li-F-C provides a compositional representation of the $Li/C_{11}F_{20}$ reaction. By using calculated reactions in Table 8, Fig. 17 can be constructed, showing schematic phase compatibilities at 1100 K. On this basis, the thermodynamically estimated oxidation reaction is:

$$C_{11}F_{20} + 20Li \rightarrow 11C + 20LiF \qquad [176]$$

As no enthalpy data have been located for $C_{11}F_{20}$, it is necessary to make an estimate. This can be done by extending the procedures used for estimating properties of hydrocarbon molecules. A very approximate value of 900 kcal/mole is obtained in this way for 298 K. The calculated enthalpy yield at 298 K is 3.1 kcal/g. Presumably the value at 1100 K would be somewhat higher.

C. <u>Safety Considerations (7)</u>

For a discussion of Li safety hazards, see Li/H_2O above. Data are not available for the $C_{11}F_{19}$ obtained, but the related compound $C_{11}F_{20}$ is a highly stable molecule which has been used to develop a synthetic blood substitute.

IX. LiB/NF_3

A. <u>Starting Materials</u>

NF_3 has been obtained from a commercial source in small cylinders.

Principal impurities are stated by the vendor as N_2, HF, NO and H_2O. A

source of LiB has been located but the material has not yet been procured,

and so there are not experimental data on the reaction at this point in time.

B. Enthalpy

In the absence of experimental data on the LiB/NF_3 reaction, thermo-

dynamic analysis of the system Li-B-N-F (Fig. 18) is essential. Using the

reactions in Table 9, the schematic 1100 K ternary phase relations in Fig. 19

have been calculated. Fig. 20 gives calculated compatibilities among product

phases at 1100 K. Table 10 gives reactions for progressive degrees of oxida-

tion of LiB fuel by NF_3. The suggested reaction for complete oxidation of

LiB by NF_3 is:

$$3LiB + 2NF_3 \rightarrow 3LiF + BN \qquad [185]$$

Boron trifluoride (BF_3) is a gas even at relatively low temperatures, and

so this would not be a desirable reaction. However by simply adding excess

lithium to the fuel, in principle the following reaction could be obtained:

$$2Li + LiB + NF_3 \rightarrow 3LiF + BN \qquad [186]$$

Depending upon the kinetics, BF_3 might still form as an intermediate product,

but the equilibrium final partial pressure would be very low. Although LiB

is known as a stable compound, thermochemical data were not available. It has

been assumed that at 1100 K it would be molten, and the ideal solution approxima-

tion has been applied to give an enthalpy of formation of 0.0 kcal. The enthalpy

yield of   reaction [180] can then be calculated as 4.6 kcal/g.

C. Safety Considerations (7)

Handling properties and toxicity of the compound LiB apparently

have not found their way into appropriate compendiums, but it is reasonable to assume that the comments made above under discussion of safety for Li and LiAl fuels would also apply here. The compound is used in pyrotechnical devices, and so there may be a potential explosion hazard. With regard to NF_3, it is a colorless gas with a moldy odor and a high toxicity similar to HF. It could therefore be expected to be extremely corrosive to the respiratory tract and skin. Prolonged exposure may cause skeletal changes.

X. Summary and Discussion

In terms of energy release/unit mass, ranking of various stored energy reactions is as in Table 11, which includes for reference, two schemes not otherwise discussed in this report:

$$Mg + H_2O \rightarrow MgO + H_2 \qquad\qquad [187a]$$

$$H_2 + (1/2)O_2 \rightarrow H_2O \qquad\qquad [187b]$$

$$2Al + 3H_2O \rightarrow Al_2O_3 + 3H_2 \qquad\qquad [188a]$$

$$3H_2 + (3/2)O_2 \rightarrow 3H_2O \qquad\qquad [188b]$$

Several points should be made regarding the ranking in Table 11. First, direct experimental evidence for several of these reactions has not yet been obtained, due in part to materials limitations. Although we are optimistic that these will soon be overcome, in the meantime the ranking

in Table 11 may have only limited practical significance. An example is
the reaction Li/H_2O [14]. Theoretically it should be high on the list
at 4.8 kcal/g. However in practice this yield may not be achieved due
to formation of LiOH, which irreversibly ties up hydrogen in the water
cycle, and reaction [13], with an enthalpy yield of 3.5 could prevail
instead. Also there are presumably other factors such as safety to be
considered. The high toxicity of beryllium makes the practicality of
utilizing reaction [169] questionable. On the other hand, it could
probably be said that since fuel or oxidant or both are inherently
chemically unstable, all of the reaction schemes involve some degree of
toxicity to human tissue or other safety hazards, and suitable safeguards
must be employed with any reaction scheme to eliminate the possibility
of containment failure or runaway reaction. For example, lithium metal
exposed to moist air at room temperature rapidly generates hydrogen.
Perchloryl fluoride has a toxic effect similar to CO. NF_3 is not only
toxic but extremely hazardous under pressure. When all such factors are
considered, undoubtedly the Mg/H_2O, $MgAl/H_2O$ and Al/H_2O schemes pose the
least safety hazard; however the latter two fuels may require very high
temperature operation to overcome the kinetic barriers to oxidation of
the aluminum. In terms of safety the $LiAl/H_2O$ scheme is also high on
the list, as LiAl is much less reactive than lithium upon exposure to
air. Furthermore from a practical viewpoint, there may be other factors
to consider besides enthalpy yield. For example, although the $Li/C_{11}F_{20}$
and Li/H_2O; NaO_2/H_2O schemes rank low in Table 11, there may be certain
advantages associated with not having to store gaseous oxidizers.

Additional experimental work is necessary at higher temperatures
than attained to date in order to verify the reactions presented in

Table 11. Evidence to date suggests several of the reactions are kin-
etically hindered at temperatures below 650 °C. We are optimistic that
the materials limitations encoutered in this preliminary study will be
overcome, so that relevant experimental data on high temperature kinetics
and phase equilibria can be systematically gathered in the near future.

XI. Future Work

The highest priority involves finding suitable container materials
so that thermogravimetric experiments can be extended to higher tempera-
tures. Rod stock of high density MgO has been obtained and is being
fabricated into crucibles. Also beryllia crucibles will be machined to
order by a vendor equipped to do this safely. Crucibles of $LiAlO_2$ have
already been fabricated. We are optimistic that use of one or more of
these materials will allow us to extend the temperature range of exper-
imentation into the 650-1000 °C region.

After the container problem is solved the first priority will be to
determine if the oxidation reactions can be made to go to completion,
and if so what the minimum temperature is at which this will occur.
Once optimum conditions for reaction are determined, an attempt will be
made to measure enthalpy of reaction directly using DTA.

Simultaneously with these experiments phase equilibrium measurements
will commence. The first experiments will involve heating the predicted
end products of the reactions together in sealed capsules, quenching and
examining to see if they really are in equilibrium as suggested by the
thermodynamically calculated reaction. This will give important information
on solubilities (both liquid and solid) as well.

It is hoped that mass spectrometric measurement of species vapor pressures during these reactions can be completed using the NBS transpiration mass spectrometry system. This apparatus allows measurements of species at pressures up to 10 atm, which would more closely simulate actual reactor conditions. Top priority would be given to the investigation of the $LiAl/ClO_3F$ and $LiAlMg/ClO_3F$ systems. Also, the $(Li + LiB)/NF_3$ and $Li/C_{11}F_{20}$ systems might be amenable to investigation by this approach.

XII. References Cited

1. SCEPS II. A New High-energy Undersea Propulsion System, Garrett Pneumatic Systems Division, Report No. 41-3675 (1982).

2. Cook, L. P., Plante, E. R., Roth, R. S., Hastie, J. W., Phase Equilibria of Stored Chemical Energy Reactants, National Bureau of Standards, Report No. NBSIR 84-2490, 112 p. (1984).

3. Costas, L. P. and Marshall, R. P., Trans. Met. Soc. AIME, 224, 971 (1962).

4. Kalakutskaya, N. A., Tepl. Vys. Temp., 6 436 (1968).

5. Levine, E. D. and Rapperport, E. J., Trans. Met. Soc. AIME, 224, 1204 (1963).

6. Stull, D. R. and Prophet, H., JANAF Thermochemical Tables, Second Ed.: U. S. Govt. Printing Office, Washington, DC, NSRDS-NBS 37, (1971). See also later supplements for 1971-1981 (J. PHys. Chem. Ref. Data).

7. Sax, N. I., Dangerous Properties of Industrial Materials (Sixth Ed.): New York, Van Nostrand, 3124 p. (1984).

8. Murray, J. L., Bull. Alloy Ph. Diag. 3 [1] 60 (1982).

9. McAlister, A. J., Bull. Alloy Ph. Diag. 3 [2] 177 (1982).

10. Moffatt, W., The Hand Book of Binary Phase Diagrams, Vol. 1: Schenectady, NY: General Electric Co. (1981 and updates).

11. Groff, E. G., Characteristics of a steadily operating metal combustor: Penn. State Univ., Ph. D. thesis, 156 p. (1976).

XIII. Appendix: Results of Literature Survey

Following are bibliographic listings which have been selected from a computerized literature search of the Chemical Abstracts Data Base (1967-1984). References are not annotated, and low temperature as well as high temperature studies have been included. References are loosely grouped according to search categories that roughly correspond to the various alternate stored chemical energy reaction fuels and oxidants.

A. Oxidation of Lithium metal, including kinetics and oxidation by water

Besson, J.and Pelloux, A., 1967, Oxidation kinetics of lithium by water
vapor: C. R. Hebd. Seances Acad. Sci., Ser. C, V. 265, No. 15,
p. 816-19.

Cooper, J. F.; Hosmer, P. K. and Homsy, R. V., 1978, The anodic behavior
of lithium in aqueous lithium hydroxide solutions: J. Electrochem.
Soc., V. 125, No. 1, p. 1-7.

Korovin, N. V. and Smirnov, S. E., 1982, Anodic oxidation of lithium in
lithium hydroxide solutions. Structure of a lithium film: Elektro-
khimiya, V. 18, No. 11, p. 1510-12.

Stone, H. E. N., 1972, Oxidation of metals in relation to the periodic
classification: J. Mater. Sci., V. 7, No. 10, p. 1147-53.

Touzain, P., 1967, Kinetic study of the oxidation of alkali metals by
dry oxygen: Commis. Energ. At. (Fr.). Rapp., No. CEA-R 3301, p. 1-93.

B. Oxidation of aluminum metal, including kinetics and oxidation by water

Agarwala, V. K. and Fort, T. Jr., 1974, Work function changes during low pressure oxidation of aluminum at room temperature: Surf. Sci., V. 45, No. 2, p. 470-82.

Agarwala, V. K and Fort, T. Jr., 1976, Nature of the stable oxide layer formed on an aluminum surface by work function measurements: Surf. Sci., V. 54, No. 1, p. 60-70.

Akimov, A. G.; Rozenfel'd, I. L. and Dagurov, V. G., 1980, X-ray electron spectroscopy study of oxidation of aluminum in oxygen and water vapor: Zashch. Met., V. 16, No. 5, p. 573-6.

Andreev, L. A.; Gel'man, B. G. and Zhukhovitskii, A. A., 1974, Absorption of hydrogen by solid aluminum during high-temperature oxidation in water vapors: Fiz-Khim. Issled. Metall. Protsessov, No. L., p. 90-94.

Bachrach, R. Z.; Flodström, S. A.; Bauer, R. S.; Hastrom, S. B. M. and Chadi, D. J., 1978, Surface resonances and the oxidation of single-crystal aluminum: J. Vac. Sci. Technol., V. 15, No. 2, p. 488-93.

Baker, B. R. and Balser, J. D., 1976, Formation of films on aluminum by reaction with water: Aluminum (Duesseldorf), V. 52, No. 3, p. 197-200.

Bakulin, E. A.; Balabanova, L. A.; Bredov, M. M. and Stepin, E. V., 1973, Characteristic electron energy losses during oxidation of aluminum films: Fiz. Tverd. Tela (Leningrad), V. 15, No. 4, p. 1266-7.

Barycka, I. and Hejduk, A., 1974, Anodic oxidation of aluminum in a d.c. oxygen discharge: Pr. Nauk. Inst. Technol. Elektron. Politech. Wroclaw., V. 11, p. 53-64.

Beck, A. F.; Heine, M. A.; Caule, E. J. and Pryor, M. J., 1967, Kinetics of the oxidation of Al in oxygen at high temperature: Corros. Sci., V. 7, No. 1, p. 1-22.

Benndorf, C.; Keller, G.; Seidel, H. and Thieme, F., 1977, High-resolution quartz oscillator microbalance and its application to the initial oxidation of aluminum: J. Vac. Sci. Technol., V. 14, No. 3, p. 819-21.

Benninghoven, A. and Mueller, A., 1972, Investigation of the surface oxidation of metals in the submonolayer and monolayer range with the static method of secondary ion mass spectrometry: Thin Solid Films, V. 12, No. 2, p. 439-42.

Bhavani, K. and Vaidyan, V. K., 1979, Asymptotic form of oxide growth for aluminum thin films: Natl. Acad. Sci. Lett. (India), V. 2, No. 12, p. 457-9.

Section B, continued

Bradshaw, A. M.; Hofmann, P. and Wyrobisch, W., 1977, The interaction of
    oxygen with aluminum (111): Surf. Sci., V. 68, p. 269-76.

Breakspere, R. J., 1970, High-temperature oxidation of aluminum in various
    gases: J. Appl. Chem., V. 20, No. 7. p. 208-12.

Bullett, D. W., 1980, The bonding of oxygen to aluminum(111): Surf.
    Sci., V. 93, No. 1, p. 213-22.

Cathcart, J. V.; Petersen, G. F. and Sparks, C. J., 1967, Oxidation rate
    and oxide structural defects: Surfaces Interfaces 1, Proc. Sagamore
    13th Army Mater. Res. Conf., Oak Ridge National Laboratory, Oak Ridge,
    TN, (Burke, J. J., Ed.), p. 333-46.

Chang, C. C.; Fraser, D. B.; Grieco, M. J.; Sheng. T. T.; Haszko, S. E.;
    Kerwin, R. E.; Marcus, R. B. and Sinha, A. K., 1978, Aluminum oxidation
    in water: J. Electrochem. Soc., V. 125, No. 5, p. 787-92.

Cox, B., 1974, Technique for studying the rate controlling processes dur-
    ing metal oxidation: Proc. 5th Int. Congr. Met. Corros., At. Energy
    Canada Ltd., Chalk River, Ont., (Sato, N., Ed.), p. 682-9.

Dickens,   C.; Heckingbottom, R. and Linnett, J. W., 1969, Oxidation of
    metals and alloys. II. Oxidation of metals by atomic and molecular
    oxygen: Trans. Faraday Soc., V. 65, No. 8, p. 2235-47.

Dong, D., 1982, Anodic oxidation treatment of aluminum reactor vessel:
    Huagong Jixie, No. 4, p. 59-62.

Eberhardt, W. and Kunz, C., 1978, Oxidation of aluminum single crystal
    surfaces by exposure to oxygen and water: Surf. Sci., V. 75, No. 4,
    p. 709-20.

Elyutin, V. P.; Mitin, B. S.; Samoteikin, V. V., 1971, Effect of oxygen
    pressure on the oxidation of aluminum: Izv. Akad. Nauk SSSR, Metal,
    V. 3, No.

Faeber, W. and Braun, P., 1975, Investigations of the oxide formation
    on metals with the Auger electron spectroscopy: Mikrochim. Acta, Suppl.,
    V. 6, p. 391-402.

Fehlner, F. P. and Mott, N. F., 1971, Low-temperature oxidation. Reply
    to discussion: Oxid. Metals, V. 3, No. 3, p. 275-7.

Flodström, S. A.; Bachrach, R. Z.; Bauer, R. S. and Hagstrom, S. B. M.,
    1977, Oxidation of aluminum single crystal faces: (100), (110), and
    (111): Proc. 7th Int. Vac. Congr., Palo Alto Res. Cent., Xerox, Palo
    Alto, CA, (Dobrozemsky, R.; Ruedenauer, F. and Viehboeck, F. P., Eds.),
    V. 2, p. 869-72.

Section B, continued

Flodström, S. A.; Martinson, C. W. B.; Kalkoffen, B. and Kunz, C., 1980, Oxygen interaction with clean aluminum and magnesium films investigated by synchrotron-radiation-induced photoemission: Mater. Sci. Eng., V. 42, No. 1, p. 31-7.

Fontijn, A.; Felder, W. and Houghton, J. J., 1973, Kinetics of aluminum atom oxidation: U. S. Nat. Tech. Inform. Serv., AD Rep., No. 776673/6GA, 34 p.

Fontijn, A.; Kurzius, S. C. and Houghton, J. J., 1972, Kinetics of metal atom oxidation reactions: U. S. Nat. Tech. Inform. Serv., AD Rep., No. 749380, 56 p.

Fridrich, J., 1971, Use of a quartz crystal microbalance to study the oxidation of aluminum during vacuum deposition: Thin Solid Films, V. 7, No. 3/4, p. 277-85.

Gerlach, J. and Weber, J., 1974, Rate of oxidation of aluminum in fused cryolite: Metall, V. 28, No. 3, p. 218-23.

Glukhov, V. I.; Fedoseev, V. A.; Grigorenko, I. N. and Kolpakova, T. I., 1979, Chemical reactions of aluminum with water: Fiz. Aerodispersn. Sistem, (Kiev), No. 19, p. 49-54.

Godard, H. P., 1967, Oxide film growth over five years on some aluminum sheet alloys in air of varying humidity at room temperature: J. Electrochem. Soc., V. 114, No. 4, p. 354-6.

Goral'nik, A. S., 1968, Kinetics of the anodic oxidation of aluminum and its alloys: Elektrokhimiya, V. 4, No. 9, p. 1108-10.

Gorbunov, V. V.; Khromov, V. G. and Shidlovskii, A. A., 1971, Oxidative activity of water vapor, carbon dioxide, and carbon monoxide toward magnesium and aluminum powders: Zh. Prikl. Khim. (Leningrad), V. 44, No. 4, p. 727-34.

Gray, T. J. and Pryor, J. M., 1969, Oxidation kinetics: Mater. Sci. Res., Coll. of Ceram., State Univ. of New York, Alfred, NY, (Gray, T. J., Ed.), V. 4, p 446-60.

Gremyachkin, V. M.; Istratov, A. G. and Leipunskii, O. I., 1974, Formation of condensed oxide particles during combustion of fine metal drops: Zh. Prikl. Mekh. Tekh. Fiz., No. 4, p. 70-8.

Grimblot, J. and Eldridge, J. M., 1982, Oxidation of aluminum films: J. Electrochem. Soc., V. 129, No. 10, p. 2369-72.

Grinbergs, M., 1975, High-temperature oxidation of aluminum: Tezisy Dokl. - 4th Konf. Molodykh Nauchn. Rab. Inst. Neorg. Khim., Akad. Nauk Latv. SSR, Inst. Neorg. Khim., Riga, USSR, (Sokolov, Yu. N., Ed.), p. 24-5.

Section <u>B</u>, continued

Hagstrom, S. B. M.; Bachrach, R. Z.; Bauer, R. S. and Flodström, S. A.,
1977, Oxidation of aluminum surfaces studied by synchrotron radiation
photoelectron spectroscopy: Phys. Scr., V. 16, No. 5-6, p. 414-19.

Hayden, B. E.; Klemperer, D. F.; Allen, G. C. and Tucker, P. M., 1980,
The early stages of oxidation of magnesium, aluminum and magnesium/
aluminum alloys: Vide, Couches Minces, V. 201, Suppl., Proc. 4th, Int.
Conf. Solid Surf., V1, p. 453-7.

Hunt, G. L. and Ritchie, I. M., 1972, Effect of pressu.e changes on the
oxidation rate of aluminum at 323-673 K: J. Chem. Soc., Faraday Trans. 1,
V. 68, Pt. 8, p. 1413-22.

Hunt, G. L. and Ritchie, I. M., 1972, Oxidation of aluminum by nitrous oxide
at 323-683 K: J. Chem., Faraday Trans. 1, V. 68, Pt. 8, p. 1423-34.

Kamel, K. H. M.; Awad, S. A. and Kassab, A., 1979, Mechanism of electro-
chemical reactions at aluminum electrodes in sodium hydroxide solutions:
J. Electroanal. Chem. Interfacial Electrochem., V. 99, No. 1, p. 121-5.

Khan, J. M. and Makowiecki, D. M., 1978, Investigation of room-temperature
oxidation of aluminum thin films by scanning high-energy electron diffraction:
Surf. Sci., V. 77, No. 1, p. L155-L161.

Kirk, C. T., Jr. and Hueer, E. E., Jr., 1968, Oxidation of aluminum films
in low-pressure oxygen atmospheres: Surf. Sci., V. 9, No. 2, p. 217-45.

Kiselev, V. I. and Lepinskikh, B. M., 1974, Kinetics of oxidation of
molten aluminum: Deposited Doc., VINITI 542-74, 12 p.

Kiselev, V. I.; Lepinskikh, B. M. and Zhuchkov, V. I., 1974, Kinetics of
liquid metal oxidation by oxygen from the gaseous phase: Tr. Inst.
Metall., Akad. Nauk SSSR, Ural. Nauchn. Tsentr., V. 28, p. 117-20.

Klei, H. E. and Stutzman, L. F., 1968, Effect of oxide thickness on the
oxidation of aluminum films: Mater. Sci. Eng., V. 3, No. 2, p. 71-5.

Krakauer, H.; Posternak, M.; Freeman, A. J. and Koelling, D. D., 1981,
Initial oxidation of the aluminum(001) surface: Self-consistent electronic
structure of clean aluminum(001) and aluminum(001)-p(1 x 1)oxygen: Phys.
Rev. B: Condens. Matter, V. 23, No. 8, p. 3859-76.

Krueger, W. H. and Pollack. S. R., 1972, Initial oxidation of aluminum
thin films at room temperature: Surface Sci., V. 30, No. 2, p. 263-79.

Labunov, V. A.; Parkhutik, V. P. and Gavrilov, I. G., 1977 Kinetics of
low temperature oxidation of metals in closed systems: Vestsi Akad.
Navuk BSSR, Ser. Fiz.-Tekh. Navuk, No. 4, p. 37-40.

Section B, continued

Labunov, V. A.; Parkhutik, V. P. and Tkharev, E. E., 1978, Model of the
    low-temperature oxidation of metals: Zh. Fiz. Khim., V. 52, No. 5,
    p. 1168-71.

Labunov, V. A.; Smirnov, A. G. and Kazantsev, A. P., 1976, Effect of con-
    ditions for carrying out plasma oxidation on the kinetics of oxide
    growth on aluminum: v sb., Nitevid. Kristally i Tonkie Plenki.,
    Ch. 2, p. 487-93.

Leitenberger, H.; Liebgott, H.; Schmidt, H. J. and Wuellenweber, H.,
    1973, Hydrogen from methanol and steam (Patent): Germany Offen.
    DE 2220617.

Lepinskikh, B. M. and Kiselev, V. I., 1974, Oxidation of liquid metals
    and alloys by oxygen from the gas phase: Izv. Akad. Nauk SSSR, Met.,
    No. 5, p. 51-4.

Levina, R. A. and Oleinikov, G. N., 1983, Contact potential difference
    study of the oxidation of aluminum: Real. Struktura i Svoistva Tverd.
    Tel, Sverdlovsk, p. 23-8.

Lokenbach, A. K.; Strods, V.; Lepins, L.; Sulce, A.; Abrams, I. and
    Zaporina, N. A., 1981, Effect of the initial state of the surface on
    oxidation kinetics of highly dispersed aluminum powders: Latv. PSR
    Zinat. Akad. Vestis, Kim. Ser., No. 1, p. 50-8.

Lokenbaha, A.; Strods, V.; Zaporina, N. A.; Abeltina, A.; Stodere, M.;
    Lepins, L. and Abrams, I., 1983, Nonisothermal oxidation of highly
    dispersed aluminum powders: Latv. PSR Zinat. Akad. Vestis, Kim. Ser.,
    No. 3, p. 310-14.

Lokenbach, A. K.; Zaporina, N. A. and Lepins, L., 1981, Phase composition
    and structure of oxide films on particles of highly dispersed aluminum
    powders: Latv. PSR Zinat. Akad. Vestis, Kim. Ser., No. 1, p. 45-9.

Maksimenko, V. I. and Maksimenko, L. S., 1973, Kinetics of oxidation of
    aluminum and its alloys in the liquid state: Nov. Teor. Tekhnol.
    Metall. Protsessov, p. 16-20.

Meierhoefer, W. and Oswald, H. R., 1972, Reaction of aluminum with molecular
    oxygen and nitrogen at temperatures between 400 and 600 deg: Therm. Anal.,
    Proc. 3rd Int. Conf., Inorg. Chem. Inst., Univ. Zurich, Zurich, Switz.,
    (Wiedemann, H. G., Ed.), V. 2, p. 409-21.

Michel, R.; Jourdan, C.; Castaldi, J. and Derrien, J., 1979, On the initial
    interaction of oxygen with the (111) and (100) aluminum surfaces: Surf.
    Sci., V. 84, No. 2, p. L509-L514.

Mitin, B. S. and Samoteikin, V. V., 1971, Oxidation of molten aluminum: Zh.
    Fiz. Khim., V. 45, No. 3, p. 730.

Section B, continued

Moskovits, M., 1972, Kinetics of oxidation of molten aluminum in oxidant streams: Oxid. Metals, V. 5, No. 1, p. 1-9.

Murata, Y. and Ohtani, S., 1972, Measurement of the growth of oxide layers on metals by low-energy electron spectroscopy. Aluminum: J. Vac. Sci. Technol., V. 9, No. 2, p. 789-91.

Natanson, M. E., 1968, Spectral analysis of surface oxidation of different metals: Dopov. Akad. Nauk Ukr. RSR, Ser. B, V. 30, No. 11, P. 1019-21.

Nevskii, O. I.; Volkov, V. I.; Grishina, E. P. and Rumyantsev, E. M., 1979, Effect of surface films on the mechanism of the anodic dissolution of aluminum: Progres. Elektrofiz. i Elektrokhim. Metody Obrab., Saratov, p. 17-21.

Oblath, S. B. and Gole, J. L, 1980, On the continuum emissions observed upon oxidation of aluminum and its compounds: Combust. Flame, V. 37, No. 3, p. 293-312.

Pitts, J. R.; Bischke, S. D.; Falconer, J. L and Czanderna, A. W., 1984, Oxide formation on aluminum in the presence of keV electrons and carbon dioxide: J. Vac. Sci. Technol., A, V. 2, No. 2, Pt. 2, p. 1000-3.

Pryor, M. J., 1971, Low-temperature oxidation. Discussion: Oxid. Metals, V. 3, No. 3, p. 271-3.

Radin, A. Ya., 1974, Oxidation of molten metals: Svoistva Rasplavl. Met., Tr. 16th Soveshch. Teor. Liteinykh Protsessov, USSR, (Gulyaev, B. B., Ed.), p. 116-22.

Severdenko, V. P.; Labunov, V. A. and Stel'makh, V. T., 1971, Kinetics of aluminum film oxidation in oxygen plasma: Khim.-Term. Obrab. Metal. Splavov, p. 154-6.

Shinohara, K.; Kyogoku, H.; Kumada, K. and Seo, T., 1980, Oxidation kinetics of aluminum single crystals in a transmission electron misroscope: Ehime Daigaku Kiyo, Shizen Kagaku, B, V. 9, No. 3, p. 781-90.

Sinaiskii, N. A., 1971, Plasma-chemical process for preparing gamma-alumina: Nizkotemp. Plazma Tekhnol. Neorg. Veshchestv, Tr, 2nd Vses. Semin., USSR, (Zhukov, M. F., Ed.).

Stolyarov, E. A., 1968, Oxidation of aluminum with water by the action of ultrasound: Zh. Prikl. Khim. (Leningrad), V. 41, No. 10, p. 2302-3.

Stone, H. E. N., 1972, Oxidation of metals in relation to the periodic classification: J. Mater. Sci., V. 7, No. 10, p. 1147-53.

Section B, continued

Szalkowski, F. J., 1982, Evidence for a molecular intermediate during the
    oxidation of aluminum by water: J. Chem. Phys., V. 77, No. 10,
    p. 5224-7.

Szczeklik, J. and Schabowska, E., 1980, Kinetics of the formation of thin
    films of aluminum oxide in a low temperature plasma: Thin Solid Films,
    V. 71, No. 1, p. L17-L19.

Vernidub, I. I.; Makolkin, I. A.; Gusev, N. I. and Abramov, Yu. A., 1968,
    Thermodynamic characteristics of the oxidation of aluminum and magnesium
    by water and water vapor: Tr., Mosk. Inst. Nar. Khoz., No. 46, p. 18-23.

Wahl, G., 1983, Coating composition and the formation of protective oxide
    layers at high temperatures: Thin Solid Films, V. 107, No. 4, P. 417-26.

Wiedmer, E. and Grauer, R., 1974, Behavior of aluminum electrodes in fluoride
    solutions: Aluminum (Duesseldorf), V. 50, No. 4, p. 268-70.

Yu, H. L.; Munoz, M. C. and Soria, F., 1980, On the initial stages of
    oxidation of aluminum (111) by LEED analysis: Surf. Sci., V. 94, No. 2-3,
    p. L184-L190.

Zhuravlev, V. A. and Zakharov, A. P., 1980, Oxidation of aluminum in water
    at different temperatures: Dokl. Akad. Nauk SSSR, V. 252, No. 5, p. 1162-6.

Zhuravlev, V. A. and Zakharov, A. P., 1980, Induction period at the initial
    stages of aluminum oxidation in water: Dokl. Akad. Nauk SSSR, V. 254,
    No. 5, p. 1155-8.

C. Reaction of LiAl alloy with water

Ichiki, M. and Ishii, M., 1973, Electrolytic purification of waste water (Patent): Germany Offen. DE 2225701.

Kanin, E. N.; Gustareva, A. A.; Brazhnikova, G. I. and Zhukova, V. P., 1978, Anodic oxidation of an aluminum-magnesium-lithium alloy: Zashchita ot Korrozii Konstruktsion. Splavov., Kuibyshev, p. 84-90.

Oda, N.; Yoshida, T.; Nakanishi, T.; Yoshikawa, K.; Adachi, A.; Ueda, J. and Mizota, A., 1974, Production of high pressure gas (Patent): Japan Kokai Tokkyo Koho JP 7447282.

Oda, T.; Yoshida, T.; Nakanishi, T.; Yoshikawa, K.; Adachi, A.; Ueda, S. and Mizota, A., 1977, Generation of a high-pressure gas propellant for self-propelled underwater vessels (Patent): Japan Tokkyo Koho JP 7727626.

Urbach, H. B.; Icenhower, D. E.; Cervi, M. C. and Bowen, R. J., 1974, Fuel cell using lithium-aluminum alloy anode and aqueous electrolyte (Patent): United States US 482980.

D. Oxidation of LiAl alloy

Carpio, R. A. and King, L. A., 1981, Deposition and dissolution of lithium-aluminum alloy and aluminum from chloride-saturated lithium chloride-aluminum chloride and sodium chloride-aluminum chloride melts: J. Electrochem. Soc., V. 128, No. 7, p. 1510-17.

Field, D. J.; Butler, E. P. and Scamans, G. M., 1981, High-temperature oxidation studies of aluminum-3 wt. % lithium, aluminum-4.2 wt. % magnesium and aluminum-3 wt. % lithium-2 wt. % magnesium alloys: Alum.-Lithium Alloys, Proc. 1st Int. Alum.-Lithium Conf., Dep. Metall. Mater. Sci., Imp. Coll., London, Engl., (Starke, E. A., Jr., Ed.), p. 325-46.

Fridlyander, I. N.; Litvintsev, A. I.; Gabidullin, R. M.; Dudkina, S. I.; Klimova, L. N. and Shiryaeva, N. V., 1968, Oxidation of alloys of an aluminum-magnesium-lithium system with a beryllium additive: Alyum. Splavy, V. 5, p. 335-41.

Fridlyander, I. N.; Sandler, V. S.; Nikol'skaya, T. I.; Savinkov, R. A. and Roshchina, I. N., 1978, Study of the near-surface layer of the aluminum alloy 01420: Izv. Akad. Nauk SSSR, Met., No. 2, p. 220-2.

Goncharov, V. I. and Breslavets, V. P., 1979, Mechanism of lithium-aluminum electrode performance: Fiz. Khim. Elektrokhim. Rasplavl. Tverd. Elektrolitov, Tezisy Dokl. Vses. 7th Konf. Fiz. Khim. Ionnykh Rasplavov Tverd. Elektrolitov, USSR, V. 2, p. 125-7.

Horski, J., 1970, Method for obtaining tritiated water from a lithium-aluminum alloy irradiated in a reactor: Nov. Metody Poluch. Radioaktiv. Prep., Sb. Dokl. Simp., Cent. Prod. Distrib. Isot., Inst. Nucl. Res., Swierk, Pol., p. 311-18.

Kanin, E. N.; Gustareva, A. A.; Brazhnikova, G. I. and Zhukova, V. P., 1978, Anodic oxidation of an aluminum-magnesium-lithium alloy: Zashchita ot Korrozii Konstruktsion. Splavo' ., Kuibyshev, p. 84-90.

Kuz'michev, L. V.; Maizlin, L. Ya.; Radin, A. Ya. and Gureev, B. D., 1976, Oxidation of aluminum-lithium alloys and methods of protection: Tekhnol. Legkikh Splavov. Nauch.-tekhn. Byul. VILSa, No. 8, p. 18-22.

L'vov, A. L.; Gnilomedov, A. A. and Protasov, E. N., 1979, Anodic oxidation of lithium-aluminum alloys in fused chlorides: Elektrokhim. Ionnykh Rasplavov, Saratov. Gos. Univ., Saratov, USSR, (Delimarskii, Yu. K., Ed.), p. 135-9.

L'vov, A. L.; Gnilomedov, A. A. and Protasov, E. N., 1979, Electrochemical behavior of lithium-magnesium, lithium-magnesium-aluminum, and lithium-silicon alloys in a lithium chloride-potassium chloride molten eutectic: Issled. v Obl. Khim. Istochnikov Toka, (Saratov), No. 6, p. 3-6.

L'vov, A. L; Gnilomedov, A. A.; Selemenev, A. P. and Protasov, E. N., 1975, Anodic dissolution of lithium-aluminum alloys in a lithium chloride-potassium chloride melt: Elektrokhimiya, V. 11, No. 9, p. 1322-4.

E. Oxidation of Magnesium metal, including kinetics and oxidation by water

Andreev, L. A.; Lunskii, M. Kh.; Gel'man, B. G. and Zhukhovitskii, A. A.,
    1973, Kinetics of exoelectron emission during the oxidation of magnesium:
    Zh. Fiz. Khim., V. 47, No. 4, p. 852-5.

Bellobono, I. R.; Mazza, F. and Cataldi, M. T., 1976, Spontaneous dissolution
    of metals in aqueous electrolytes. II. Kinetics of the reaction of magnesium
    and zinc with hydrochloric acid solutions: Gazz. Chim. Ital., V. 106, No. 3-6,
    p. 259-65.

Benninghoven, A. and Wiedmann, L., 1974, Investigation of surface reactions by
    the static method of secondary ion mass spectrometry. IV. Oxidation of
    magnesium, strontium, and barium in the monolayer range: Surface Sci.,
    V. 40, No. 2, p. 483-92.

Bloshenko, V. N.; Merzhanov, A. G. and Khaikin, B. I, 1976, Determination of
    the kinetic parameters of the high-temperature oxidation of magnesium: Fiz.
    Goreniya Vzryva, V. 12, No. 5, p. 682-8.

Cismaru, D. and Simon, Z., 1969, Kinetics of the formation of oxide layers
    on metals: Rev. Roum. Chim., V. 14, No. 7, p. 837-43.

Faeber, W. and Braun, P., 1975, Investigations of the oxide formation on
    metals with the Auger electron spectroscopy: Mikrochim. Acta, Suppl., V. 6,
    p. 391-402.

Felder, W., 1981, Kinetics of some metal atom and metal fluoride oxidation
    reactions relevant to Air Force technology development: AeroChem Res. Lab.
    Inc., Princeton, NJ, Report No. AEROCHEM-TP-411, AFOSR-TR-81-0599, 20 p.

Flodström, S. A.; Martinson, C. W. B.; Kalkoffen, G. and Kunz, C., 1980,
    Oxygen interaction with clean aluminum and magnesium films investigated
    by synchrotron-radiation-induced photoemission: Mater. Sci. Eng., V. 42,
    No. 1, p. 31-7.

Frishberg, I. V. and Mikulinskii, A. S., 1966, Comparison of oxidizability
    of metallic powders prepared by condensation and mechanically: Tr. Inst.
    Metall., Sverdlovsk, V. 11, p. 49-53.

Fuggle, J. C.; Watson, L. M.; Fabian, D. J. and Affrossman, S., 1975, X-ray
    photoelectron studies of the reaction of clean metals (magnesium, aluminum,
    chromium, manganese) with oxygen and water vapor: Surf. Sci., V. 49, No. 1,
    p. 61-76.

Gorbunov, V. V.; Khromov, V. G. and Shidlovskii, A. A., 1971, Oxidative
    activity of water vapor, carbon dioxide, and carbon monoxide toward magnesium
    and aluminum powders: Zh. Prikl. Khim. (Leningrad), V. 44, No. 4, p. 727-34.

Glushkov, V. E. and Fedoseeva, N. V., 1966, Ignition of magnesium particles in
    steam: Fiz. Goreniya, I. I. Mechnikov Odessk. Gos. Univ., Odessa, USSR,
    p. 37-41.

Section E, continued

Grasselli, R. K.; Suresh, D. D. and Hardman, H. F., 1976, Oxidation catalyst
(Patent): Germany Offen. DE 2530959.

Hayashi, S. and Saito, H., 1972, Growth of fibrous magnesia via the vapor phase:
Yogyo Kyokai Shi, V. 80, No. 8, p. 319-23.

Hayden, B. E.; Klemperer, D. F.; Allen, G. C. and Tucker, P. M., 1980, The
early stages of oxidation of magnesium, aluminum and magnesium/aluminum
alloys: Vide, Couches Minces, V. 201, Suppl., Proc. 4th Int. Conf. Solid
Surf., V1, p. 453-7.

Hayden, B. E.; Schweizer, E.; Koetz, R. and Bradshaw, A. M., 1981, The early
stages of oxidation of magnesium single crystal surfaces: Surf. Sci., V. 111,
No. 1, p. 26-38.

Hodgson, A. and Machie, J. C., 1979, A shock-tube study of the kinetics of
evaporation and oxidation of magnesium: Combust. Flame, V. 35, No. 3, p. 323-34.

Kashireninov, O. E.; Kuznetsov, V. A. and Manelis, G. B., 1974, Kinetics of
the gas-phase reaction of magnesium with oxygen: AIAA Pap., V. 74-145, 8 p.

Kashireninov, O. E.; Manelis, G. B. and Repka, L. F., 1982, Refinement of
kinetic constants for the oxidation of alkaline earth metal vapors: Zh. Fiz.
Khim., V. 56, No. 4, p. 1030-1.

Kashireninov, O. E. and Osherov, V. I., 1981, Polanyi-Semenov rule in gas-phase
reactions of alkaline earth metals: Dokl. Akad. Nauk SSSR, V. 257, No. 3,
p. 636-40.

Koetz, R.; Hayden, B.; Schweizer, E. and Bradshaw, A. M., 1981, The application
of spectroscopic ellipsometry to the oxidation of magnesium: Surf. Sci.,
V. 112, No. 3, p. 229-40.

Kovalev, G. I.; Gogitidze, L. D.; Kuranova, V. I. and Denisov, E. T., 1979,
Kinetics of the oxidation of fuels in the presence of structural materials:
Neftekhimiya, V. 19, No. 2, p. 237-43.

Lea, C. and Molinari, C., 1984, Magnesium diffusion, surface segregation and
oxidation in aluminum-magnesium alloys: J. Mater. Sci., V. 19, No. 7,
p. 2336-52.

Markstein, G. H., 1968, Study of the reaction of magnesium vapor and oxygen at
the surface of magnesia deposits by atomic-absorption spectrophotometry:
Purdue Univ., Lafayette, IN, U. S. Clearinghouse Fed. Sci. Tech. Inform., AD,
No. AD-672575, 34 p.

Namba, H.; Darville, J. and Gilles, J. M., 1980, Oxidation of single crystal-
line magnesium (0001) studied by ELS, AES, LEED and work function measurements:
Vide, Couches Minces, V. 201, Suppl., Proc. 4th Int. Conf. Solid Surf., V1,
p. 470-3.

Section E, continued

Namba, H.; Darville, J. and Gilles, J. M., 1981, A model for the oxidation of
   magnesium (0001) based upon LEED, AES, ELS and work function measurements:
   Surf. Sci., V. 108, No. 3, p. 446-82.

Natanson, M. E., 1968, Spectral analysis of surface oxidation of different
   metals: Dopov. Akad. Nauk Ukr. RSR, Ser. B, V. 30, No. 11, p. 1019-21.

Ponomarenko, A. M.; Bondarev, B. I. Ivanov, V. S., 1978, Kinetics of liquid
   magnesium oxidation in an atmosphere of air and argon with sulfur dioxide
   and sulfur hexafluoride additives: Tekhnol. Legk. Splavov, No. 8, p. 3-8.

Sarrazin, P. and Besson, J., 1966, Kinetics of magnesium oxidation by dry
   oxygen at 350-450 degrees. Pressure dependence: Metallurgie (Mons, Belg.),
   V. 6, No. 1, p. 11-15.

Selivanov, S. E., 1971, Oxidation of magnesium in nitrous oxide: Fiz.
   Aerodispersnykh Sist., No. 4, p. 62-6.

Sergeev, G. B.; Smirnov, V. V.; Zagorskaya, O. V.; Zagorskii, V. V. and
   Popov, A. V., 1982, Low-temperature reaction of magnesium atoms and carbon
   dioxide: Vestn. Mosk. Univ., Ser. 2: Khim., V. 23, No. 3, p. 232-6.

Shevtsov, V. I. and Fursov, V. P., 1983, Study of the mechanism of oxida-
   tion of magnesium: Fiz. Goreniya Vzryva, V. 19, No. 4, p. 99-102.

Stone, H. E. N., 1972, Oxidation of metals in relation to the periodic clas-
   sification: J. Mater. Sci., V. 7, No. 10, p. 1147-53.

Svettsov, V. I. and Labirev, V. L., 1981, Calculation of process rates
   during the plasma reaction-thermal deposition of oxide films: USSR,
   Deposited Doc., Report No. SPSTL 61 khp-D81, 21 p.

Tetere, A.; Steina, D.; Lokenbah, A.; Lepins, L. and Abrams, I., 1976,
   Oxidation of magnesium hydrosol: Latv. PSR Zinat. Akad. Vestis, Kim.
   Ser., No. 5, p. 564-8.

Tiunov, V. S.; Mamaev, V. I. and Morachevskii, A. G., 1979, Study of the
   electrochemical behavior of lithium-magnesium alloys in a lithium chloride-
   potassium chloride molten electrolyte: Fiz. Khim. Elektrokhim. Rasplavl.
   Tverd. Elektrolitov, Tezisy Dokl. Vses. 7th Konf. Fiz. Khim. Ionnykh Rasplavov
   Tverd. Elektrolitov, V. 2, 122 p.

Tseluikina, G. V. and Abakhaev, M. G., 1981, Electrochemical behavior of
   magnesium in liquid ammonia media: Khim. Istochniki Toka, Novocherkassk,
   p. 50-6.

Vale, R. and Smallman, R. E., 1977, An x-ray topographic study of the be-
   havior of vacancy loops formed during the high-temperature oxidation of
   magnesium crystals: Philos. Mag., V. 36, No. 1, p. 209-23.

Section E, continued

Vernidub, I. I.; Makolkin, I. A.; Busev, N. I. and Abramov, Yu. A., 1968,
Thermodynamic characteristics of the oxidation of aluminum and magnesium
by water and water vapor: Tr., Mosk. Inst. Nar. Khoz., No. 46, p. 18-22.

Williams, R. E. and Kottenstette, J. P., 1967, Approach to combustion kinetics -
new technique: West. States Sect., Combust. Inst. (Pap.), No. 67-27, 14 p.

F. Oxidation of aluminum-magnesium alloy, including kinetics and oxidation
by water

Anthony, W. H. and Rasmussen, T. S., 1976, Corrosion-resistant aluminum com-
posite material (Patent): Germany Offen. DE 2458201.

Baranov, N. S.; Lotsmanov, S. N.; Stepanov, G. A.; Getalov, S. P.; Red'kin, L. A.;
Lokhmatov, B. V.; Egorov, V. M. and Shlyamneva, I. A., 1970, Alloy for de-
hydration of molten salts (Patent): USSR SU 270462.

Boehmer, M. and Munz, D., 1975, Fatigue of an aluminum-magnesium alloy (AlMg$_3$)
in gases of different pressures. I. Fatigue life measurements: Z. Metallkd.,
V. 66, No. 6, p. 329-33.

Boehmer, M. and Munz, D., 1975, Fatigue of an aluminum-magnesium (AlMg$_3$)
in gases of different pressures. II. Surface studies and fractography:
Z. Metallkd., V. 66, No. 6, p. 333-7.

Boehmer, M. and Munz, D., 1975, Fatigue of the aluminum alloy AlMg$_3$ in gases of
different pressures. III. Gas-metal interaction during fatigue: Z. Metallkd.,
V. 66, No. 7, p. 416-21.

Case, B.; Bradford, P. M. and Garbett, K., 1977, Silicate and the aqueous
corrosion of a high-magnesium alloy: Nature (London), V. 268, No. 5617,
p. 223-5.

Cherepakhova, G. L. and Shreider, A. V., 1972, Effect of the ions of cooling
waters on the pitting corrosion of an aluminum-magnesium alloy: Zh.
Prikl. Khim. (Leningrad), V. 45, No. 9, p. 1958-63.

Cochran, C. N.; Belitskus, D. L. and Kinosz, D. L., 1976, Oxidation of
aluminum-magnesium melts in air, oxygen, flue gas, and carbon dioxide:
Light Met., Proc. Sess., AIME Ann. Meet., V. 2, p. 203-27.

Ford, F. P., 1972, Stress corrosion-resistant aluminum-magnesium alloy (Patent):
Germany Offen. DE 2114209.

Gavra, Z.; Hadari, Z. and Mintz, M. H., 1981, Effects of nickel and indium
ternary additions on the hydrogenation of magnesium-aluminum intermetallic
compounds: J. Inorg. Nucl. Chem., V. 43, No. 8, p. 1763-8.

Gorbunov, V. V.; Vasil'ev, A. V. and Shidlovskii, A. A., 1959, Combustion
of mixtures of high-energy metal powders with water: Izv. Vyssh. Ucheb.
Zaved., Khim. Khim. Tekhnol., V. 12, No. 9, p. 1171-4.

Grauer, R. and Schmoker, P., 1976, The oxidation of aluminum-magnesium alloys
in oxygen at elevated temperatures: Werkst. Korros., V. 27, No. 11, p. 769-74.

Haginoya, I. and Fukusako, T., 1984, Influence of water vapor on the oxida-
tion of molten aluminum-magnesium alloys: Imono, V. 56, No. 5, p. 264-8.

Section F, continued

Hayden, B. E.; Klemperer, D. F.; Allen, G. C. and Tucker, P. M., 1980, The early stages of oxidation of magnesium, aluminum and magnesium/aluminum alloys: Vide, Couches Minces, V. 201, Suppl., Proc. 4th Int. Conf. Solid Surf., V1, p. 453-7.

Kovalenko, A. I., 1979, Electrochemical characteristics of anode alloys in stratal water: Korroz. Zashch. Neftegazov. Prom-sti., No. 7, p. 16-19.

Kuznetsov, D. A.; Notkin, E. B. and Malakhov, A. I., 1969, Effect of some factors on the quantity and chemical composition of evolving gases during sand mold casting of aluminum-magnesium alloys: Tr. Mosk. Khim.-Tekhnol. Inst., No. 60, p. 254-6.

Lepinskikh, B. M. and Belousov, A. A., 1975, Study of the kinetics of oxidation of magnesium-aluminum alloys in a molten state: Deposited Doc., VINITI 554-76, 12 p.

Maischak, K. D. and Feige, W., 1970, Causes and prevention of aluminum-water explosions: Neue Huette, V. 15, No. 11, p. 662-5.

Makovichuk, Yu. I. and Psarev, V. I., 1976, Agglomeration kinetics of beta-phase particles in aluminum-magnesium alloys: Nekotor. Vopr. Fiz. Kinet. Tverd. Tel, No. 2, p. 35-63.

Mima, G. and Yamaguchi, M., 1964, Isothermal softening spectrum of cold drawn aluminum alloys with 2 weight % magnesium. Optical microscopic observations and kinetics of isothermal softening: Nippon Kinzoku Gakkaishi, V. 28, p. 710-16.

Mintz, M. H.; Malkiely, S.; Gavra, Z. and Hadari, Z., 1978, Effect of Group IIIA metal additives on the kinetics of magnesium hydride formation: J. Inorg. Nucl. Chem., V. 40, No. 11, p. 1949-51.

Nair. C. G. K., 1983, Kinetics of magnesium loss during melting/holding of aluminum-magnesium alloys: Trans. Indian Inst. Met., V. 36, No. 4-5, p. 351-3.

Nikitina, M. F.; Fadeeva, G. N. and Romashin, V. M., 1966, Oxidation kinetics of aluminum-magnesium alloys: Tr., Mosk. Aviats. Tekhnol. Inst., No. 67, p. 65-78.

Pagetti, J., 1972, New device for studying passivation of metals and alloys: AVIRES 2, Colloq. 2nd Int. Appl. Sci. Tech. Vide Revetements Etats Surface, C. R., Lab. Genie Chim., Ec. Natl. Super. Chim. Paris, Fr., p. 174-88.

Psarev, V. I. and Kulikov, A. F., 1977, Kinetics of the coalescence of disperse beta-phase of aluminum-magnesium alloys. I: Izv. Vyssh. Uchebn. Zaved., Fiz., V. 20, No. 12, p. 46-51.

Radin, A. Ya., 1974, Oxidation of molten metals: Svoistva Rasplavl. Met., 16rh Tr. Soveshch. Teor. Liteinykh Protsessov, USSR (Gulyaev, B. B., Ed.), p. 116-22.

Section F, continued

Ryum, N. and Embury, J. D., 1982, A comment on the recrystallization behavior of aluminum-magnesium: Scand. J. Metall., V. 11, No. 2, p. 51-4.

Shimogori, K.; Fujiwara, K. and Komura, M., 1974, Corrosion-resistant aluminum alloy useful as heat exchanger tube material (Patent): Japan Kokai Tokkyo Koho JP 7458013.

Shrieder, A. V. and Cherepakhova, G. L., 1972, Reversal of polarity during the contact corrosion of aluminum-magnesium alloys: Zh. Prikl. Khim. (Leningrad), V. 45, No. 7, p. 1603-4.

Tuck, C. D. S. and Scamans, G. M., 1982, Hydrogen embrittlement of aluminum-zinc-magnesium and aluminum-magnesium alloys: Hydrogene Mater., 3rd Congr. Int., Alcan Int. Ltd., Banbury, UK (Azou, P., Ed.), V. 2, p. 665-70.

G. Lithium-beryllium alloys

Alekseevskii, N. E. and Zakosarenko, V. M., 1973, Superconductivity of
  beryllium alloys: Dokl. Akad Nauk SSSR, V. 208, No. 2, p. 303-6.

Fridlyander, I. N.; Gulin, A. N.; Sandler, V. S.; Yatsenko, K. P.; Kolesnikova,
  V. I.; Polyakov, E. S. and Yudin, A. F., 1971, Deformable alloy based
  on aluminum (Patent): USSR SU 310946.

Griffiths, L. B., 1969, Fine-grained, ductile beryllium-aluminum-magnesium-
  silicon composites obtained by chill-mold casting under argon using lithium
  chloride and fluoride as flux (Patent): France FR 1567093, 9 p.

Krock, R. H.; Larsen, E. I. and Jones, C. R., 1967, Alloys of beryllium with
  aluminum magnesium (Patent): United States US 3323880, 5 p.

Krock, R. H.; Larsen, E. I. and Jones, C. R., 1967, Alloys of beryllium with
  silver and aluminum (Patent): United States US 3322512, 5 p.

Nishimura, M., 1971, Beryllium-containing metal filler for welding aluminum
  (Patent): Japan Tokkyo Koho JP 7139452, 2 p.

TRW Inc., 1968, Controlled heat production by the reaction of sulfur hexa-
  fluoride with lithium (Patent): France FR 1526940, 3 p.

Pauliukonis, R. S., 1967, Sulfur hexafluoride-lithium fuel (Patent): United
  States US 3325318, 2 p.

H.   Lithium-boron alloys

Bischof, J.; Dlouhy, Z,; Kvitek, V. and Vobecky, M., 1972, Determination
of boron and lithium in materials by an (n, alpha) nuclear reaction:
Jad. Energ., V. 18, No. 9, p. 269-8.

Born, E. and Loewedey, R., 1975, Diffusion of the products of the nuclear
reaction 10B(n, alpha)7Li and hydrogen in single crystals of beta-
rhombohedral boron: Atomkernenergie, V. 26, No. 4, p. 283-4.

Born, E.; Krahl, J. and Loewedey, R., 1975, Distribution of lithium in
surface layers of neutron irradiated boron crystals and its change fol-
lowing heat treatment: Atomkernenergie, V. 26, No. 1, p. 58-60.

Dallek, S., Ernst, D. W. and Larrick, B. F., 1979, Thermal analysis of
lithium-boron alloys: J. Electrochem. Soc., V. 126, No. 5, p. 866-70.

Dallek, S.; Larrick, B. F. and Szwarc, R., 1982, Lithium-boron alloy anodes
for thermally activated batteries: Proc. Power Sources Symp., V. 30,
p. 42-5.

De Vries, R. C. and Fleischer, J. F., 1972, Cubic boron nitride preparation
from lithium-boron-nitrogen mixtures (Patent): United States US 3701826.

DeVries, L. E. and Gubner, E., 1978, Determination of main components and
impurities in lithium-boron alloys: Anal. Chem., V. 50, No. 6, p. 694-8.

Dzhakhandarov, Sh. D.; Rza-Zade, P. F.; Samedov, F. R. and Eyubova, N. A.,
1975, Phase diagram of the lithium oxide-boron oxide-cobalt(II) oxide
$(Li_2O.B_2O_3-CoO)$ system: Azerb. Khim. Zh., No. 4, p. 116-18.

Ernst, D., 1982, DSC study of two reactions in the lithium-boron alloy system:
J. Electrochem. Soc., V. 129, No. 7, p. 1513-15.

Ferguson, I. F.; Masters, D. R. and Turek, M., 1983, The Auger spectra of
lithium metal and "oxidized lithium": Salwick/Preston, UK, North, Div.
Rep. ND-R - U. K. At. Energy Auth., Report No. ND-R-463(S), 26 p.

Itoh, M.; Sato, S. and Yokokawa, T., 1976, E.m.f. measurements of molten
mixtures of lithium oxide +, sodium oxide +, and potassium oxide + boron
oxide: J. Chem. Thermodyn., V. 8, No. 4, p. 339-52.

James, S. D., 1981, Comparison of anodic dischargability of lithium-boron
alloy with pure lithium in lithium carbide (LiClO)4-propylene carbonate:
Naval Surface Weapons Cent., Silver Spring, MD, Report No. NSWC/TR-81-155,
SBI-AD-F500015, 27 p.

James, S. D., 1982, Comparison of anodic dischargeability of lithium-boron
alloy with pure lithium in lithium perchlorate-propylene carbonate:
J. Appl. Electrochem., V. 12, No. 3, p. 317-21.

Section H, continued

James, S. D. and De Vries, L. E., 1976, Structure and anodic discharge
behavior of lithium-boron alloys in the lighium chloride-potassium chloride
eutectic melt: J. Electrochem Soc., V. 123, No. 3, p. 321-7.

Kezuka, H. and Iwamura, K., 1982, Studies of thin films of lithium-boron
alloys: Appl. Surf. Sci., V. 11-12, No. 1-3, p. 144-8.

Kilroy, W. P. and Angres, I., 1979, The extraction and determination of
free lithium in lithium-boron alloys: J. Less-Common Met., V. 63, No. 1,
p. 123-8.

Larrick, B. F.; James, S. D. and Szwarc, R., 1978, Lithium-boron alloy -
a new battery anode material: Proc. - Power Sources Symp., V. 28th, p. 95-8.

Lewis, H. L, 1980, Exothermic IR source materials. Lithium-boron alloy
materials: Nav. Weapons Support Cent., Crane, IN, Report No. NWSC/CR/RDTR-134,
18 p.

Lewis, H. L., 1982, Thermogravimetric analysis of reactivity of an air-reactive
alloy of lithium and boron: Proc. Int. Pyrotech. Semin., V. 8, p. 446-65.

McManis, G. E.; Miles, M. H. and Fletcher, A. N., 1984, The lithium-boron
alloy anode in molten nitrate electrolytes: J. Electrochem. Soc., V. 131,
No. 2, p. 286-9.

Mestwerdt, R. and Selzer, H., 1976, Experimental investigation of boron/lithium
combustion: AIAA J., V. 14, No. 1, p. 100-2.

Mitchell, M. A. and Sutula, R. A., 1978, The density, electrical resistivity
and Hall coefficient of lithium-boron alloys: J. Less-Common Met., V. 57,
No. 2, p. 161-75.

Nakamura, S. and Hayashi, H., 1975, Compounds in a lithium oxide-boron
oxide-water system: Yogyo Kyokai Shi, V. 83, No. 1, p. 38-45.

Schleyer, P. v. R., 1983, Are lithium carbide (CLi_6), lithium nitride (NLi_5),
lithium oxide (OLi_4), etc., hypervalent?: New Horiz. Quantum Chem., Proc.
4th Int. Congr. Quantum Chem.; Friedrich-Alexander-Univ. Erlangen-Nurnberg,
Erlangen, Germany (Loewdin, P.-O. and Pullman, B., Ed.), p. 95-109.

Samedov, F. R.; Rzazade, P. F. and Abdullaev, G. K., 1970, The $Li_2O.B_2O_3$-
Ga_2O_3 system: Izv. Akad. Nauk SSSR, Neorg. Mater., V. 6, No. 5, P. 1030-1.

Secrist, D. R., 1967, Compound formation in the systems lithium-carbon and
lithium boron: J. Am. Ceram. Soc., V. 50, No. 10, p. 520-3.

Selzer, H., 1975, Use of lithium boride (LiB_2) in pyrotechnic fires: Pyrotech.:
Grundlagen, Technol. Anwend., Jahrestag., Inst. Chem. Treib-Explosivst.
Fraunhofer-Ges., Bremen, Germany, p. 99-107.

Section H, continued

Simons, D. G.; Land, D. J.; Brown, M. D. and Brennan, J. G., 1980, Ion Beam
analysis of lithium-boron alloys: White Oak Lab., Nav. Surf. Weapons Cent.,
Silver Spring, MD, Report No. NSWC/TR-79-95, 18 p.

Sutula, R. A. and Wang, F. E., 1979, Battery with boron-lithium alloy anode
(Patent): United States US 4162352.

Szwarc, R. and Dallek, S., 1982, Lithium-boron (Li(B)) ingot preparation
scale-up study: Gen. Electr. Co., St. Petersburg, FL, Report No. GEPP-
TM-645, 44 p.

Szwarc, R.; Walton, R. D.; Dallek, S. and Larrick, B. F., 1982, Discharge
characteristics of lithium-boron alloy anode in molten salt thermal cells:
J. Electrochem. Soc., V. 129, No. 6, p. 1168-73.

Vakhtin, B. S. and Filippov, E. M., 1972, Differential determination of
boron and lithium by the neutron-resonance method: Zh. Anal. Khim.,
V. 27, No. 3, p. 595-7.

Wang, F. E., 1978, Ductile lithium-boron alloys (Patent): United States
US 4110111, 4 p.

Wang, F. E., 1979, An unusual phenomenon in the formation of lithium-boron
(Li_5B_4) compound-alloy: Metall. Trans., A, V. 10A, No. 3, p. 343-8.

I. Perchloryl fluoride and nitrogen trifluoride

Adcock, W. and Khor, T. C., 1975, Perchloryl fluoride. Further warning:
J. Organomet. Chem., V. 91, No. 1, p. C20.

Alekseev, V. I.; Fedorova, L. I. and Baluev, A. V., 1983, Mass-spectro-
metric study of thermochemical characteristics of perchloryl fluoride
and its decomposition product chlorosyl fluoride: Izv. Akad. Nauk SSSR,
Ser. Khim., No. 5, p. 1084-90.

Anderson, D. G.; England, D. C. and Milian, A. D., Jr., 1981, Fluorinated
carbonyl compounds (Patent): Germany Offen. DE 3032471.

Aubert, J.; Bougon, R. and Carles, M., 1967, Hydrolysis of chlorine tri-
fluoride, chlorine monofluoride, and chloryl fluoride. Study of the for-
mation of perchloryl fluoride: Commis. Energ. At. (Fr.), Rapp., V. CEA-R
3282, 19 p.

Barberi, P., 1973, Enthalpy of combustion and formation of oxychlorofluoride
compounds: Bull. Inform. Sci. Tech., Cow.is. Energ. At. (Fr.), V. No. 180,
p. 55-60.

Barberi, P., 1977, Contribution to the study of chlorine, fluorine and oxygen
compounds: CEN Saclay, CEA, Gif-sur-Yvett, Fr., Report No. CEA-R-4771, 157 p.

Beardell, A. J. and Grelecki, C. J., 1968, Perchloryl fluoride (Patent):
United States US 3404958.

Beresneva, I. V.; Mamynov, V. V. and Tukhvatullin, A. M., 1983, Logarithmic
dependence of the heat capacity of individual substances on temperature:
Zh. Fiz. Khim., V. 57, No. 2, p. 285-8.

Blackburn, G. M.; England, D. A. and Kolkmann, F., 1981, Monofluoro- and
difluoromethylenebisphosphonic acids: isopolar analogs of pyrophosphoric
acid: J. Chem. Soc., Chem. Commun., No. 17, p. 930-2.

Bougon, R.; Carles, M. and Aubert, J., 1967, Reaction between chlorine tri-
fluoride and water: C. R. Hebd. Seances Acad. Sci., Ser. C, V. 265, No. 3,
p. 179-82.

Britton, D.; Farooq, S. and Keese, R., 1977, Synthesis and structure of
fluorotricyanomethane: Helv. Chim. Acta, V. 60, No. 4, p. 1393-7.

Cady, G. H., 1978, Solubility and reactions of perchloryl fluoride in water:
J. Fluorine Chem., V. 11, No. 3-4, p. 225-41.

Cartwright, M. and Woolf, /. A., 1979, A redetermination of the heat of forma-
tion of perchloryl fluoride: J. Fluorine Chem., V. 13, No. 4, p. 353-64.

Christe, K. O.; Curtis, E. C.; Sawodny, W.; Hartner, H. and Fogarasi, G., 1981,
The general valence force field of perchloryl fluoride: Spectrochim. Acta,
Part A, V. 37A, No. 7, p. 549-56.

Section $\underline{I}$, continued

Claassen, H. H. and Appelman, E. H., 1970, Vibrational spectra and structures of perbromyl and perchloryl fluorides: Inorg. Chem., V. 9, No. 3, p. 622-4.

Clark, A. H.; Beagley, B. and Cruickshank, D. W. J., 1968, Structural parameters of perchloryl fluoride and perchloric acid: Chem. Commun., No. 1, p. 14-15.

Clark, A. H.; Beagley, B.; Cruickshank, D. W. J. and Hewitt, T. G., 1970, Electron diffraction investigation of gaseous perchloryl fluoride and calculation of its force field and amplitudes of vibration: J. Chem. Soc. A, No. 6, p. 872-5.

Clark, R. J. H. and Rippon, D. M., 1974, Vapor phase Raman spectra, Raman band contour analyses, Coriolis constants, force constants, and thermodynamic functions of symmetric top molecules phosphoryl fluoride, phosphoryl chloride, trifluorooxovanadium, trichlorooxovanadium, thiophosphoryl chloride, and fluorine chlorate: Mol. Phys., V. 28, No. 2, p. 305-19.

DeLeon, R. L. and Muenter, J. S., 1980, Stark effect and dipole moment of perchloryl fluoride: J. Mol. Spectrosc., V. 83, No. 2, p. 469-70.

DeKock, R. L.; Lloyd, D. R.; Hillier, I. H. and Saunders, V. R., 1972, Experimental and theoretical study of the electronic structures of sulfuryl fluoride and perchloryl fluoride: Proc. Roy. Soc., Ser. A, V. 328, No. 1574, p. 401-11.

Dersch, R. and Reichardt, C., 1982, Syntheses with aliphatic dialdehydes. XXXIII. Attempts to synthesize difluoromalonaldhyde: Liebigs Ann. Chem., No. 7, p. 1330-47.

Dersch, R. and Reichardt, C., 1982, Syntheses with aliphatic dialdehydes. XXXIV. Attempts to synthesize bromo- or chlorofluoromalonaldehyde and fluoro(methyl)- or fluoro(phenyl)malonaldehyde: Liebigs Ann. Chem., No. 7, p. 1348-58.

Farrar, T. C.; Maryott, A. A. and Malmberg, M. S., 1971, Pulsed NMR study of rotational diffusion in perchloryl fluoride: Ber. Bunsenges. Phys. Chem., V. 75, No. 3/4, p. 246-7.

Green, J.; Levine, N. B. and Sheehan, W., 1966, Elastomers resistant to rocket propellants: Rubber Chem. Technol., V. 39, No. 4, p. 1222-32.

Guest, M. F. and Hillier, I. H., 1972, Localized orbital calculations of the bonding in SO_{2-4}, SO_2F_2, ClO_3F and $SOCl_2$: Int. J. Quantum Chem., V. 6, No. 5, p. 967-73.

Kamley, M. J., 1971, Explosive and/or propellant compounds containing a fluorodinitromethyl group (Patent): United States US 3624129.

Section I, continued

Khutoretskii, V. M.; Okhlobystina, L. V. and Fainzil'berg, A. A., 1967,
  Perchloryl fluoride (production, physical properties, reactions): Usp.
  Khim., V. 36, No. 3, p. 377-98.

Kliegel, J. R.; Gold, P. I. and Weekley, C. T., 1969, Chemical species and
  chemical reactions of importance in nonequilibrium rocket engine perfor-
  mance calculations: Pyrodynamics, V. 6, No. 3-4, p. 257-73.

Mohan, S.; Ravikumar, K. G.; Boopathy, T. J. and Chandraprakash, N., 1984,
  Normal coordinate analysis of some axially symmetric XYZ3 type molecules:
  Indian J. Phys., B, V. 58B, No. 1, p. 56-60.

Mountfield, K. R. and Weir, R. D., 1977, Low temperature heat capacity,
  dielectric constant, and thermodynamic properties of solid perchloryl
  fluoride: J. Chem. Phys., V. 66, No. 2, p. 736-42.

Nagarajan, G. and Redmon, M. J., 1972, Quantum mechanical studies of atomic,
  bond, and molecular polarizabilities, spectroscopic studies of vibrational
  constants, and statistical thermodynamics. Perchloryl and perbromyl
  fluorides: Monatsh. Chem., V. 103, No. 5, p. 1406-26.

Ostorero, J., 1970, Measurements of the viscosity of some gaseous fluorine
  compounds: Commis. Energ. At., Saclay, Fr., Report No. CEA-N-1293, 36 p.

Pilipovich. D.; Rogers, H. H. and Wilson, R. D., 1972, Chlorine trifluoride
  oxide. II. Photochemical synthesis: Inorg. Chem., V. 11, No. 9, p. 2192-5.

Ripmeester, J. A.; Garg, S. K. and Davidson, D. W., 1978, Molecular reorienta-
  tion in solid perchloryl fluoride: J. Chem. Phys., V. 69, No. 5, p. 2265-7.

Rips, S. M.; Zercheninov, A. N. and Pankratov, A. V., 1969, Detection of the
  thermodynamic properties of some fluorine and chlorine compounds: Zh. Fiz.
  Khim., V. 43, No. 2, p. 386-9.

Rogers, H. H. and Pilipovich, D., 1973, Oxychlorine trifluoride (Patent):
  United States US 3718557.

Rosolovskii, V. Ya. and Nikitin, I. V., 1972, Nitrogen oxyfluorides. Chlorine
  oxyfluorides. (Collection of reviews): Inst. Nov. Khim. Probl., Cherno-
  golovka, USSR. Report No. VINITI 5437-73, Deposited Publ., 70 p.

Rutt, H. N., 1980, Optically pumped laser action in perchloryl fluoride: Opt.
  Commun., V. 34, No. 3, p. 434-8.

Sheppard, W. A., 1969, Mechanism of fluorination by perchloryl fluoride:
  Tetrahedron Lett., No. 2, p. 83-4.

So, S. P. and Chau, F. T., 1973, Urey-Bradley force field of perhalyl fluorides:
  Z. Phys. Chem. (Frankfurt am Main), V. 85, No. 1-4, p. 69-75.

Section I, continued

Streng, A. G., 1971, Miscibility and compatibility of some liquefied and solid-
z ified gases at low temperatures: J. Chem. Eng. Data, V. 16, No. 3, p. 357-9.

Sunder, S.; Hallin, K. E. and McClung, R. E. D., 1974, Raman studies of
molecular reorientation in liquid perchloryl fluoride: J. Chem. Phys.,
V. 61, No. 7, p. 2920-4.

Sunder, S. and McClung, R. E. D., 1974, Raman spectra of polycrystalline
perchloryl fluoride: Can. J. Phys., V. 52, No. 22, p. 2299-302.

Takano, K.; Hosoya, H. and Iwata, S., 1982, Analysis of the oxidation state
and oxidation number by ab initio molecular orbital calculations: chlorine
and sulfur compounds: J. Am. Chem. Soc., V. 104, No. 14, p. 3998-4005.

Tantot, G., 1976, Structural study of some halogen oxyfluorides: CEN Saclay,
CEA, Gif-sur-Yvette, Fr., Report No. CEA-R-4770, 237 p.

Vereshchagin, A. N.; Vigalok, I. V.; Aliksandrova, L. K. and Petrova, G. G.,
1981, Polarity and polarizability of some perchloryl compounds: Izv. Akad.
Naul SSSR, Ser. Khim., No. 2, p. 257-61.

Vigalok, A. A.; Petrova, G. G.; Lukashina, S. G. and Vigalok, I. V., 1982,
Study of the reaction of perchloryl fluoride with halide ions: Zh. Neorg.
Khim., V. 27, No. 8, p. 1931-4.

Vigalok, I. V.; Petrova, G. G. and Lukashina, S. G., 1983, Salts of the
organic fluoronitrogen cation - 1-fluoro-1-alkyl-2,2,6,6-te-tramethyl-
z piperidinium: Zh. Org. Khim., V. 19, No. 6, p. 1347-8.

Wamser, C. A.; Fox, W. B.; Gould, D. and Sukornick, B., 1968, Preparation of
perchloryl fluoride by acid solvolysis of perchlorates in fluorinated solvents:
Inorg. Chem., V. 7, No. 9, p. 1933-5.

Wamser, C. A.; Sukornick, B.; Fox, W. B. and Gould, D., 1973, Nontransition-
z metal compounds. Perchloryl fluoride: Inorg. Syn., V. 14, p. 29-33.

Yodis, A. W. and Cunningham, W. J., 1968, Production of perchloryl fluoride
(Patent): United States US 3375072.

Ziebell, G. and Gross, H., 1978, Aromatic perchloryl compounds (Patent):
Patent No. Germany (East) DD 132391.

J. Fluorocarbon ($C_{11}F_{20}$)

Chambers, R. D.; Taylor, G. and Powell, R. L, 1980, Reactions involving
    Fluoride ion. Part 18. Derivatives of perfluoro cycloalkenes: J. Chem.
    Soc., Perkin Trans. 1, No. 2, p. 429-34.

Clark, L. C., Jr.; Moore, R. E.; Diver, S. and Miller, M. L., 1979, A new
    look at the vapor pressure problem in red cell substitutes: Int. Congr.
    Ser. - Excerpta Med., V. 486, Proc. 4th Int. Symp. Perfluorochem. Blood
    Substitutes, 1978, p. 55-67.

Cottrell, D. W., 1970, Fluorocarbon dielectric coolants and their applications:
    Dielec. Mater., Meas. Appl., Conf., Imp. Smelting Corp. Ltd., Avonmouth,
    Engl., p. 322-7.

Irving, J. B. and Jamieson, D. T., 1975, Thermal conductivity of 13 fluoro-
    carbon liquids: J. Fluorine Chem., V. 5, No. 5, p. 449-56.

Lee, R.; Devotta, S. and Holland, F. A., 1984, Derived thermodynamic design
    data for Rankine power cycle systems operating on PP9: J. Heat Recovery
    Syst., V. 4, No. 1, p. 51-6.

Moore, R. E.; Clark, L. C., Jr. and Miller, M. L., 1979, Synthesis and
    biological activity of perfluoroadamantane and some closely related compounds:
    Int. Congr. Ser. - Excerpta Med., V. 486, Proc. 4th Int. Symp. Perfluorochem.
    Blood Substitutes, 1978, p. 69-79.

Morini, A.; Macchi, E. and Giglioli, G., 1980, Experimental results on the
    thermal stability of some fluorocarbons: Proc. Intersoc. Energy Convers.
    Eng. Conf., V. 15, No. 2, p. 992-7.

Nakamura, Y.; Umemura, H. and Yonekura, M., 1975, Emulsions of fluorine-
    containing compounds (Patent): Japan Kokai Tokkyo Koho JP 75121184.

Nelson, J. K. and Manterfield, R. J., 1977, Sparking potentials in fluoro-
    carbons vapors: Proc. Inst. Electr. Eng., V. 124, No. 6, p. 586-8.

Suntech, Inc., 1980, Determination of critical solution temperatures of per-
    fluorocarbons (Patent): Japan Kokai Tokkyo Koho JP 8095868.

Wesseler, E. P.; Iltis, R. and Clark, L. C., Jr., 1977, The solubility of
    oxygen in highly fluorinated liquids: J. Fluorine Chem., V. 9, No. 2,
    p. 137-46.

Yokoyama, K.; Naito, R.; Tsuda, Y.; Fukaya, C.; Watanabe, M.; Hanada, S.
    and Suyama, T., 1983, Selection of 53 PFC substances for better stability
    of emulsion and improved artificial blood substitutes: Prog. Clin. Biol.
    Res., V. 122, Adv. Blood Substitute Research, p. 189-96.

Section <u>J</u>, continued

Yokoyama, K.; Suyama, T.; Okamoto, H.; Watanabe, M.; Ohyanagi, H. and Saitoh, Y., 1984, A perfluorochemical emulsion as an oxygen carrier: Artif, Organs, V. 8, No. 1, p. 34-40.

Yokoyama, K.; Yamanouchi, K.; Murashima, R. and Tsuda, Y., 1976, Oxygen-transferable fluorocarbon emulsion (Patent): United States US 654964.

Yonekura, M.; Nagase, S.; Baba, H.; Kodaira, K. and Abe, T., 1976, The electro-chemical fluorination of trifluoromethyl-substituted benzenes: Bull. Chem. Soc. Jpn., V. 49, No. 4, p. 1113-16.

XIV. Tables

Table 1. X-ray Diffraction Analysis of $LiAl/ClO_3F$ Experimental Products

Expt.	Max Temp.	%Wt. Gain	Phases
TGA	650 °C (isothermal)	109.86	$\alpha\text{-}Li_3AlF_6$, LiF*, AlF_3, Al
TGA	550 °C (isothermal)	97.58	Al, $\beta\text{-}Li_3AlF_6$, AlF_3, LiF
TGA	450 °C (isothermal)	98.52	Al, $\beta\text{-}Li_3AlF_6$, AlF_3, LiF, (LiCl)
TGA	350 °C (isothermal)	109.26	Al, AlF_3, Li_3AlF_6,
Mass Spec.	900 °C (non-isothermal)	---	$\gamma LiAlO_2$, Al
TGA	650 °C (non-isothermal)	91.69	αLi_3AlF_6, AlF_3, Al, LiF
TGA	650 °C Partial React. (isothermal)	50.43	LiCl, Al, LiAl, $\gamma LiAlO_2$, LiF

*LiF apparently contains a small amount LiCl in solid solution, as judged by x-ray line shifts

Table 2. Progressive Oxidation of LiAl alloy by Reaction with Components of ClO_3F

Reaction #	Type of Reaction	Reaction	Final Wt. Gain at Completion
[24]	chlorination	$LiAl + ClO_3F \rightarrow LiCl + Al + (3/2)O_2 + (1/2)F_2$	+0.51
[25]	chlorination	$LiAl + 4ClO_3F \rightarrow LiCl + AlCl_3(g) + 6O_2 + 2F_2$	+0.25
[26]	fluorination	$LiAl + ClO_3F \rightarrow LiF + Al + (3/2)O_2 + (1/2)Cl_2$	+0.56
[27]	fluorination	$3LiAl + 6ClO_3F \rightarrow Li_3AlF_6 + 2Al + 9O_2 + 3Cl_2$	+1.12
[28]	fluorination	$3LiAl + 12ClO_3F \rightarrow Li_3AlF_6 + 2AlF_3 + 18O_2 + 6F_2$	+2.24
[29]	oxygenation	$3LiAl + 2ClO_3F \rightarrow 3LiAlO_2 + Cl_2 + F_2$	+0.94
[30]	chlorination & oxygenation	$5LiAl + 2ClO_3F \rightarrow 3LiAlO_2 + 2LiCl + 2Al + F_2$	+0.98
[31]	chlorination & oxygenation	$7LiAl + 4ClO_3F \rightarrow 3LiAlO_2 + 4LiCl + 2Al_2O_3 + 2F_2$	+1.41
[32]	fluorination & oxygenation	$5LiAl + 2ClO_3F \rightarrow 3LiAlO_2 + 2LiF + 2Al + Cl_2$	+0.79
[33]	fluorination & oxygenation	$7LiAl + 4ClO_3F \rightarrow 3LiAlO_2 + 4LiF + 2Al_2O_3 + Cl_2$	+1.12
[34]	chlorination & fluorination	$2LiAl + ClO_3F \rightarrow LiCl + LiF + 2Al + (3/2)O_2$	+0.80
[35]	chlorination & fluorination	$9LiAl + 6ClO_3F \rightarrow 6LiCl + Li_3AlF_6 + 8Al + 9O_2$	+1.07
[36]	chlorination & fluorination	$3LiAl + 6ClO_3F \rightarrow 3LiCl + 2AlF_3 + AlCl_3(g) + 9O_2$	+1.90
[37]	chlorination & fluorination & oxygenation	$7LiAl + 2ClO_3F \rightarrow 2LiCl + 3LiAlO_2 + 2LiF + 4Al$	+0.86
[38]	chlorination & fluorination & oxygenation	$2LiAl + ClO_3F \rightarrow Al_2O_3 + LiF + LiCl$	+1.51

Table 3. Calculated Phase Compatibilities in System Li-Al-O-Cl-F at 1100 K

Reaction #	Subsystem	Reaction	ΔG_R(1100 K), kcal
[39]	$Li_2O-Al_2O_3-Li-Al$	$2Li_2O(c) + LiAl(\ell) \rightarrow LiAlO_2(c) + 4Li(\ell)$	- 9.6
[40]	$Li_2O-Al_2O_3-Li-Al$	$2Li_2O(c) + Al(\ell) \rightarrow LiAlO_2(c) + 3Li(\ell)$	- 11.1
[41]	$Li_2O-Al_2O_3-Li-Al$	$3Li(\ell) + 2Al_2O_3(c) \rightarrow 3LiAlO_2(c) + Al(\ell)$	- 47.6
[42]	$Li_2O-Al_2O_3-Li-Al$	$3LiAlO_2(c) + 2Al(\ell) \rightarrow 2Al_2O_3(c) + 3LiAl(\ell)$	+ 43.1
[43]	$Li_2O-Al_2O_3-Li-Al$	$3Li_2O(c) + 2LiAl(\ell) \rightarrow 8Li(\ell) + Al_2O_3(c)$	+ 10.1
[44]	$Li_2O-Al_2O_3-Li-Al$	$Al_2O_3(c) + 6LiAl(\ell) \rightarrow 3Li_2O(c) + 8Al(\ell)$	+ 2.0
[45]	$Li_2O-Al_2O_3-Li-Al$	$LiAlO_2(c) + 3LiAl(\ell) \rightarrow 2Li_2O(c) + 4Al(\ell)$	+ 15.7
[46]	$Li_2O-Al_2O_3-Li-Al$	$3LiAlO_2(c) + LiAl(\ell) \rightarrow 2Al_2O_3(c) + 4Li(\ell)$	+ 49.2
[47]	$Li_2O-Al_2O_3-Li-Al$	$3Li_2O(c) + 2Al(\ell) \rightarrow Al_2O_3(c) + 6Li(\ell)$	+ 7.1
[48]	$Li_2O-Al_2O_3-LiCl-AlCl_3$	$2Li_2O(c) + AlCl_3(g) \rightarrow LiAlO_2(c) + 3LiCl(\ell)$	-117.5
[49]	$Li_2O-Al_2O_3-LiCl-AlCl_3$	$6LiCl(\ell) + Al_2O_3(c) \rightarrow 3Li_2O(c) + 2AlCl_3(g)$	+205.6
[50]	$Li_2O-Al_2O_3-LiCl-AlCl_3$	$3LiCl(\ell) + 2Al_2O_3(c) \rightarrow 3LiAlO_2(c) + AlCl_3(g)$	+ 58.7
[51]	$LiCl-AlCl_3-LiF-AlF_3$	$3LiCl(\ell) + AlF_3(c) \rightarrow 3LiF(c) + AlCl_3(g)$	+ 32.7
[52]	$LiCl-AlCl_3-LiF-AlF_3$	$3LiCl(\ell) + Li_3AlF_6(\ell) \rightarrow 6LiF(c) + AlCl_3(g)$	+ 44.1
[53]	$LiCl-AlCl_3-LiF-AlF_3$	$Li_3AlF_6(\ell) + AlCl_3(g) \rightarrow 3LiCl(\ell) + 2AlF_3(c)$	- 21.4
[54]	$LiCl-AlCl_3-Li-Al$	$3LiAl(\ell) + AlCl_3(g) \rightarrow 3LiCl(\ell) + 4Al(\ell)$	-101.8
[55]	$LiCl-AlCl_3-Li-Al$	$4Li(\ell) + AlCl_3(g) \rightarrow 3LiCl(\ell) + LiAl(\ell)$	-107.9
[56]	$LiCl-AlCl_3-Li-Al$	$3LiCl(\ell) + Al(\ell) \rightarrow 3Li(\ell) + AlCl_3(g)$	+106.4

Table 3 (continued)

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[57]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	6LiF(c) + Al$_2$O$_3$(c) → 3Li$_2$O(c) + 2AlF$_3$(c)	+140.2
[58]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	LiAlO$_2$(c) + Li$_3$AlF$_6$(ℓ) → 2Li$_2$O(c) + 2AlF$_3$(c)	+ 96.1
[59]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	3LiAlO$_2$(c) + Li$_3$AlF$_6$(ℓ) → 6LiF(c) + 2Al$_2$O$_3$	− 14.7
[60]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	3LiAlO$_2$(c) + AlF$_3$(c) → 3LiF(c) + 2Al$_2$O$_3$(c)	− 26.0
[61]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	LiAlO$_2$(c) + 3LiF(c) → 2Li$_2$O(c) + AlF$_3$(c)	+ 84.8
[62]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	2Li$_3$AlF$_6$(ℓ) + 3Li$_2$O(c) → 12LiF(c) + Al$_2$O$_3$(c)	−117.5
[63]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	Li$_3$AlF$_6$(ℓ) + 2Li$_2$O(c) → 6LiF(c) + LiAlO$_2$(c)	− 73.4
[64]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	2Li$_3$AlF$_6$(ℓ) + Al$_2$O$_3$(c) → 3Li$_2$O(c) + 4AlF$_3$(c)	+162.8
[65]	Li$_2$O-Al$_2$O$_3$-LiF-AlF$_3$	Li$_3$AlF$_6$(ℓ) + 2Al$_2$O$_3$(c) → 3LiAlO$_2$(c) + 2AlF$_3$(c)	+ 37.3
[66]	LiF-AlF$_3$-Li-Al	3Li(ℓ) + AlF$_3$(c) → 3LiF(c) + Al(ℓ)	− 73.6
[67]	LiF-AlF$_3$-Li-Al	Li$_3$AlF$_6$(ℓ) + 3LiAl(ℓ) → 6LiF(c) + 4Al(ℓ)	− 57.8
[68]	LiF-AlF$_3$-Li-Al	4Li(ℓ) + 2AlF$_3$(c) → Li$_3$AlF$_6$(ℓ) + LiAl(ℓ)	− 86.5
[69]	LiF-AlF$_3$-Li-Al	3LiAl(ℓ) + AlF$_3$(c) → 3LiF(c) + 4Al(ℓ)	− 69.1
[70]	LiF-AlF$_3$-Li-Al	Li$_3$AlF$_6$(ℓ) + Al(ℓ) → 3Li(ℓ) + 2AlF$_3$(c)	+ 85.0
[71]	LiF-AlF$_3$-Li-Al	Li$_3$AlF$_6$(ℓ) + 4Al(ℓ) → 2AlF$_3$(c) + 3LiAl(ℓ)	+ 80.4
[72]	LiFAlF$_3$LiAl	Li$_3$AlF$_6$(ℓ) + 3Li(ℓ) → 6LiF(c) + Al(ℓ)	− 62.3
[73]	LiF-AlF$_3$-Li-Al	LiAl(ℓ) + 3Li → 4Li(ℓ) + AlF$_3$(c)	+ 75.1
[74]	LiF-AlF$_3$-Li-Al	LiAl(ℓ) + 6LiF(c) → 4Li(ℓ) + Li$_3$AlF$_6$(ℓ)	+ 63.8

Table 4. Calculated Phase Compatibilities in System Li-Al-Mg-O-Cl-F at 1100 K

Reaction #	Subsystem	Reaction	$\Delta G_R(1100\ K)$, kcal
[75]	$MgO-Li_2O-MgF_2-LiF$	$MgO(c) + 2LiF(\ell) \rightarrow Li_2O(c) + MgF_2(c)$	+ 28.1
[76]	$MgO-Li_2O-MgCl_2-LiCl$	$MgO(c) + 2(MgCl_2 \cdot LiCl)(\ell) \rightarrow 3MgCl_2(\ell) + Li_2O(c)$	+ 52.2
[77]	$MgO-Li_2O-MgCl_2-LiCl$	$MgO(c) + 2LiCl(\ell) \rightarrow MgCl_2(\ell) + Li_2O(c)$	+ 49.1
[78]	$MgO-Li_2O-MgCl_2-LiCl$	$MgO(c) + 3LiCl(\ell) \rightarrow (MgCl_2 \cdot LiCl)(\ell) + Li_2O(c)$	+ 47.6
[79]	$Mg-Li-MgO-Li_2O$	$2Mg(\ell) + Li_2O(c) \rightarrow 2MgLi(\ell) + MgO(c)$	- 9.8
[80]	$Mg-Li-MgO-Li_2O$	$Mg(\ell) + LiO_2(c) \rightarrow MgO(c) + 2Li(\ell)$	- 6.8
[81]	$Mg-Li-MgO-Li_2O$	$MgO(c) + 3Li(\ell) \rightarrow MgLi(\ell) + Li_2O(c)$	+ 5.3
[82]	$MgF_2-LiF-MgCl_2-LiCl$	$3MgCl_2(\ell) + 2LiF(\ell) \rightarrow 2(MgCl_2 \cdot LiCl)(\ell) + MgF_2(c)$	- 24.1
[83]	$MgF_2-LiF-MgCl_2-LiCl$	$3LiCl(\ell) + MgF_2(c) \rightarrow (MgCl_2 \cdot LiCl)(\ell) + 2LiF(c)$	+ 19.6
[84]	$MgF_2-LiF-MgCl_2-LiCl$	$MgCl_2(\ell) + 2LiF(c) \rightarrow 2LiCl(\ell) + MgF_2(c)$	- 21.1
[85]	$Mg-Al-MgO-Al_2O_3$	$3MgO(c) + 2MgAl(\ell) \rightarrow 5Mg(\ell) + Al_2O_3(c)$	+ 30.6
[86]	$Mg-Al-MgO-Al_2O_3$	$4MgO(c) + 2MgAl(\ell) \rightarrow 5Mg(\ell) + MgAl_2O_4(c)$	+ 22.6
[87]	$Mg-Al-MgO-Al_2O_3$	$4MgO(c) + 2Al(\ell) \rightarrow MgAl_2O_4(c) + 3Mg(\ell)$	+ 19.5
[88]	$Mg-Al-MgO-Al_2O_3$	$3MgAl_2O_4(c) + 2Al(\ell) \rightarrow 3Mg(\ell) + 4Al_2O_3(c)$	+ 51.6
[89]	$Mg-Al-MgO-Al_2O_3$	$3MgAl_2O_4(c) + 5Al(\ell) \rightarrow 4Al_2O_3(c) + 3MgAl(\ell)$	+ 47.0
[90]	$Mg-Al-MgO-Al_2O_3$	$3MgO(c) + 3Al(\ell) \rightarrow Al_2O_3(c) + 3MgAl(\ell)$	+ 23.0

Table 4 (continued)

Reaction #	Subsystem	Reaction	ΔG_R(1100 K), kcal
[91]	Mg-Al-MgO-Al$_2$O$_3$	MgAl$_2$O$_4$(c) + 3MgAl(ℓ) → 4MgO(c) + 5Al(ℓ)	- 15.0
[92]	Mg-Al-MgO-Al$_2$O$_3$	3MgAl$_2$O$_4$(c) + 2MgAl(ℓ) → 5Mg(ℓ) + 4Al$_2$O$_3$(c)	+ 54.6
[93]	Mg-Al-MgO-Al$_2$O$_3$	3MgO(c) + 2Al(ℓ) → 3Mg(ℓ) + Al$_2$O$_3$(c)	+ 27.5
[94]	Mg-Al-MgF$_2$-AlF$_3$	3MgF$_2$(c) + 2Al(ℓ) → 2AlF$_3$(c) + 3Mg(ℓ)	+ 83.5
[95]	Mg-Al-MgF$_2$-AlF$_3$	3MgF$_2$(c) + 5Al(ℓ) → 2AlF$_3$(c) + 3MgAl(ℓ)	+ 79.0
[96]	Mg-Al-MgF$_2$-AlF$_3$	5Mg(ℓ) + 2AlF$_3$(c) → 3MgF$_2$(c) + 2MgAl(ℓ)	- 86.5
[97]	Mg-Al-MgCl$_2$-AlCl$_3$	5Mg(ℓ) + 2AlCl$_3$(g) → 3MgCl$_2$(ℓ) + 2MgAl(ℓ)	- 88.8
[98]	Mg-Al-MgCl$_2$-AlCl$_3$	3MgCl$_2$(ℓ) + 2Al(ℓ) → 3Mg(ℓ) + 2AlCl$_3$(g)	+ 85.8
[99]	Mg-Al-MgCl$_2$-AlCl$_3$	3MgCl$_2$(ℓ) + 5Al(ℓ) → 3MgAl(ℓ) + 2AlCl$_3$(g)	+ 81.2
[100]	MgF$_2$-AlF$_3$-MgCl$_2$-AlCl$_3$	MgCl$_2$(ℓ) + AlF$_3$(c) → MgF$_2$(c) + AlCl$_3$(g)	+ 56.3
[101]	Mg-Li-MgF$_2$-LiF	3Mg(ℓ) + 2LiF(c) → MgF$_2$(c) + 2MgLi(ℓ)	+ 18.2
[102]	Mg-Li-MgF$_2$-LiF	MgLi(ℓ) + 2LiF(c) → MgF$_2$(c) + 3Li(ℓ)	+ 22.8
[103]	Mg-Li-MgF$_2$-LiF	MgF$_2$(c) + 2Li(ℓ) → 2LiF(c) + Mg(ℓ)	- 21.2
[104]	MgO-Al$_2$O$_3$-MgCl$_2$-AlCl$_3$	4MgO(c) + AlCl$_3$(g) → MgCl$_2$(ℓ) + MgAl$_2$O$_4$(c)	+ 33.0
[105]	MgO-Al$_2$O$_3$-MgCl$_2$-AlCl$_3$	3MgCl$_2$(ℓ) + Al$_2$O$_3$(c) → 3MgO(c) + 2AlCl$_3$(g)	+ 58.2
[106]	MgO-Al$_2$O$_3$-MgCl$_2$-AlCl$_3$	3MgAl$_2$O$_4$(c) + 2AlCl$_3$(g) → 3MgCl$_2$(ℓ) + 4Al$_2$O$_3$(c)	- 34.2

Table 4 (continued)

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[107]	MgO-Al$_2$O$_3$-MgF$_2$-AlF$_3$	3MgF$_2$(c) + MgAl$_2$O$_4$(c) → 4MgO(c) + 2AlF$_3$(c)	+ 64.0
[108]	MgO-Al$_2$O$_3$-MgF$_2$-AlF$_3$	3MgO(c) + 2AlF$_3$(c) → 3MgF$_2$(c) + Al$_2$O$_3$(c)	− 56.0
[109]	MgO-Al$_2$O$_3$-MgF$_2$-AlF$_3$	2AlF$_3$(c) + 3MgAl$_2$O$_4$(c) → 3MgF$_2$(c) + 4Al$_2$O$_3$(c)	− 31.9
[110]	Mg-Li-MgCl$_2$-LiCl	3MgCl$_2$(ℓ) + 2Li(ℓ) → 2(MgCl$_2$·LiCl)(ℓ) + Mg(ℓ)	− 45.4
[111]	Mg-Li-MgCl$_2$-LiCl	MgCl$_2$(ℓ) + 2Li(ℓ) → Mg(ℓ) + 2LiCl(ℓ)	− 42.3
[112]	Mg-Li-MgCl$_2$-LiCl	(MgCl$_2$·LiCl)(ℓ) + 2Li(ℓ) → 3LiCl(ℓ) + Mg(ℓ)	− 40.8
[113]	MgO-Al$_2$O$_3$-Li$_2$O-MgCl$_2$-AlCl$_3$-LiCl	MgCl$_2$(ℓ) + 2LiAlO$_2$(c) → MgAl$_2$O$_4$(c) + 2LiCl(ℓ)	− 27.8
[114]	MgO-Al$_2$O$_3$-Li$_2$O-MgF$_2$-AlF$_3$-LiF	MgF$_2$(c) + 2LiAlO$_2$(c) → MgAl$_2$O$_4$(c) + 2LiF(c)	− 6.7
[115]	MgO-Al$_2$O$_3$-Li$_2$O-MgF$_2$-AlF$_3$-LiF	Li$_3$AlF$_6$(ℓ) + 3MgAl$_2$O$_4$(c) → 3LiAlO$_2$(c) + 3MgF$_2$(c) + 2Al$_2$O$_3$(c)	+ 5.4
[116]	MgO-Al$_2$O$_3$-Li$_2$O-MgF$_2$-AlF$_3$-LiF	2Li$_3$AlF$_6$(ℓ) + 6MgAl$_2$O$_4$(c) → 6MgF$_2$(c) + 6LiAlO$_2$(c) + 4Al$_2$O$_3$(c)	+ 10.8
[117]	MgO-Al$_2$O$_3$-Li$_2$O-MgF$_2$-AlF$_3$-LiF	Li$_3$AlF$_6$(ℓ) + 2MgO → 2LiF(c) + 2MgF$_2$(c) + LiAlO$_2$(c)	− 17.3

Table 4 (continued)

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[118]	MgF_2-AlF_3-LiF-$MgCl_2$-$AlCl_3$-$LiCl$	$3MgCl_2(\ell) + 2Li_3AlF_6(\ell) \rightarrow 6LiCl(\ell) + 3MgF_2(c) + 2AlF_3(c)$	-40.6
[119]	Mg-Al-Li-MgF_2-AlF_3-LiF	$2Li_3AlF_6(\ell) + 3Mg(\ell) \rightarrow 6LiF(c) + 3MgF_2(c) + 2Al(\ell)$	-60.9
[120]	Mg-Al-Li-MgO-Al_2O_3-Li_2O	$LiAlO_2(c) + 2Mg(\ell) \rightarrow 2MgO(c) + LiAl(\ell)$	-4.0
[121]	Mg-Al-Li-MgO-Al_2O_3-Li_2O	$MgAl_2O_4(c) + 2Li(\ell) \rightarrow 2LiAlO_2(c) + Mg(\ell)$	-14.6
[122]	Mg-Al-Li-MgO-Al_2O_3-Li_2O	$2MgAl_2O_4(c) + 3Li(\ell) \rightarrow 2MgO(c) + 3LiAlO_2(c) + Al(\ell)$	-31.6

Table 5. Progressive Oxidation of LiAlMg alloy by reaction with Components of ClO_3F

Reaction #	Type of Reaction	Reaction
[123]	chlorination	$LiAlMg + ClO_3F \rightarrow Mg + Al + LiCl + (1/2)F_2 + (3/2)O_2$
[124]	chlorination	$LiAlMg + 3ClO_3F \rightarrow MgCl_2 + LiCl + Al + (3/2)F_2 + (9/2)O_2$
[125]	chlorination	$LiAlMg + 6ClO_3F \rightarrow LiCl + MgCl_2 + AlCl_3(g) + 3F_2 + 9O_2$
[126]	fluorination	$LiAlMg + ClO_3F \rightarrow Mg + Al + LiF + (1/2)F_2 + (3/2)O_2$
[127]	fluorination	$3LiAlMg + 12ClO_3F \rightarrow 3MgF_2 + Li_3AlF_6 + 2Al + 6Cl_2 + 18O_2$
[128]	fluorination	$3LiAlMg + 18ClO_3F \rightarrow 3MgF_2 + 2AlF_3 + Li_3AlF_6 + 9Cl_2 + 27O_2$
[129]	oxygenation	$LiAlMg + (2/3)ClO_3F \rightarrow Mg + LiAlO_2 + (2/3)Cl_2 + (1/3)F_2$
[130]	oxygenation	$LiAlMg + ClO_3F \rightarrow MgO + LiAlO_2 + (1/2)Cl_2 + (1/2)F_2$
[131]	chlorination & oxygenation	$7LiAlMg + 6ClO_3F \rightarrow 6LiCl + 3MgAl_2O_4 + LiAlO_2 + 4MgO + 3F_2$
[132]	fluorination & oxygenation	$7LiAlMg + 6ClO_3F \rightarrow 6LiF + 3MgAl_2O_4 + LiAlO_2 + 4MgO + 3Cl_2$
[133]	chlorination & fluorination	$LiAlMg + 3ClO_3F \rightarrow LiCl + AlF_3 + MgCl_2 + (9/2)O_2$
[134]	chlorination & fluorination & oxygenation	$4LiAlMg + 3ClO_3F \rightarrow MgF_2 + LiF + 3LiCl + 2MgAl_2O_4 + MgO$

Table 6. Calculated Phase Compatibilities in System Li-Be-O-Cl-F at 1100 K

Reaction #	Subsystem	Reaction	ΔG_R(1100 K), kcal
[135]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + Li_2BeF_4(\ell) \rightarrow 4LiF(c) + Be(c)$	− 28.3
[136]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + 4LiBeF_3(\ell) \rightarrow 3Li_2BeF_4(\ell) + Be(c)$	− 42.1
[137]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + LiBeF_3(\ell) \rightarrow 3LiF(c) + Be(c)$	− 31.7
[138]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + BeF_2(\ell) \rightarrow 2LiF(c) + Be(c)$	− 38.6
[139]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + 2BeF_2(\ell) \rightarrow Li_2BeF_4(\ell) + Be(c)$	− 48.9
[140]	$Li-Be-LiF-BeF_2$	$2Li(\ell) + 3BeF_2(\ell) \rightarrow 2LiBeF_3(\ell) + Be(c)$	− 52.2
[141]	$Li_2O-BeO-LiF-BeF_2$	$Li_2O(c) + Li_2BeF_4(\ell) \rightarrow 4LiF(c) + BeO(c)$	− 39.7
[142]	$Li_2O-BeO-LiF-BeF_4$	$Li_2O(c) + 4LiBeF_3(\ell) \rightarrow 3Li_2BeF_4(\ell) + BeO(c)$	− 53.5
[143]	$Li_2O-BeO-LiF-BeF_4$	$Li_2O(c) + LiBeF_3(\ell) \rightarrow 3LiF(c) + BeO(c)$	− 43.1
[144]	$Li_2O-BeO-LiF-BeF_4$	$Li_2O(c) + BeF_2(\ell) \rightarrow 2LiF(c) + BeO(c)$	− 50.0
[145]	$Li_2O-BeO-LiF-BeF_4$	$Li_2O(c) + 2BeF_2(\ell) \rightarrow BeO(c) + Li_2BeF_4(\ell)$	− 60.3
[146]	$Li_2O-BeO-LiF-BeF_4$	$Li_2O(c) + 3BeF_2(\ell) \rightarrow BeO(c) + 2LiBeF_3(\ell)$	− 63.6
[147]	$Li-Be-LiCl-BeCl_2$	$2LiCl(\ell) + Be(c) \rightarrow BeCl_2(g) + 2Li(\ell)$	+ 63.9
[148]	$Li-Be-Li_2O-BeO$	$2Li(\ell) + BeO(c) \rightarrow Li_2O(c) + .e(c)$	+ 11.4
[149]	$Li_2O-BeO-LiCl-BeCl_2$	$Li_2O(c) + BeCl_2(g) \rightarrow 2LiCl(\ell) + BeO(c)$	− 75.3
[150]	$LiCl-BeCl_2-LiF-BeF_2$	$2LiCl(\ell) + Li_2BeF_4(\ell) \rightarrow 4LiF(c) + BeCl_2(g)$	+ 35.6

Table 6 (continued)

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[151]	LiCl-BeCl$_2$-LiF-BeF$_2$	2LiCl(ℓ) + LiBeF$_3$(ℓ) $\rightarrow$ 3LiF(c) + BeCl$_2$(g)	+ 32.1
[152]	LiCl-BeCl$_2$-LiF-BeF$_2$	2LiCl(ℓ) + BeF$_2$(ℓ) $\rightarrow$ 2LiF(c) + BeCl$_2$(g)	+ 25.3
[153]	LiCl-BeCl$_2$-LiF-BeF$_2$	Li$_2$BeF$_4$(ℓ) + BeCl$_2$(g) $\rightarrow$ 2LiCl(ℓ) + 2BeF$_2$(ℓ)	- 15.0
[154]	LiCl-BeCl$_2$-LiF-BeF$_2$	2LiCl(ℓ) + 4LiBeF$_3$(ℓ) $\rightarrow$ 3Li$_2$BeF$_4$(ℓ) + BeCl$_2$(g)	+ 21.8
[155]	LiCl-BeCl$_2$-LiF-BeF$_2$	2LiBeF$_3$(ℓ) + BeCl$_2$(g) $\rightarrow$ 2LiCl(ℓ) + 3BeF$_2$(ℓ)	- 11.6

Table 7. Progressive Oxidation of (Li+Be) Fuel by Reaction with Components of ClO_3F

Reaction #	Type of Reaction	Reaction
[156]	fluorination	$Li + Be + ClO_3F \rightarrow LiF + Be + (1/2)Cl_2 + (3/2)O_2$
[157]	fluorination	$Li + Be + 2ClO_3F \rightarrow LiF + BeF_2 + Cl_2 + 3O_2$
[158]	chlorination	$Li + Be + ClO_3F \rightarrow LiCl + Be + (1/2)F_2 + (3/2)O_2$
[159]	chlorination	$Li + Be + 3ClO_3F \rightarrow LiCl + BeCl_2(g) + (3/2)F_2 + (9/2)O_2$
[160]	oxygenation	$3Li + 3Be + ClO_3F \rightarrow 3Li + 3BeO + (1/2)Cl_2 + (1/2)F_2$
[161]	oxygenation	$3Li + 3Be + ClO_3F \rightarrow (3/2)Li_2O + 3BeO + (1/2)Cl_2 + (1/2)F_2$
[162]	fluorination & oxygenation	$3Li + 3Be + ClO_3F \rightarrow LiF + 2Li + 3BeO + (1/2)Cl_2$
[163]	fluorination & oxygenation	$3Li + 3Be + ClO_3F \rightarrow 2Li_2O + 3BeO + (1/2)Cl_2 + (1/2)F_2$
[164]	chlorination & oxygenation	$3Li + 3Be + ClO_3F \rightarrow 2Li + 3BeO + LiCl + (1/2)F_2$
[165]	chlorination & oxygenation	$7Li + 7Be + 3ClO_3F \rightarrow 2Li_2O + 3LiCl + 7BeO + (3/2)F_2$
[166]	chlorination & fluorination	$2Li + 2Be + ClO_3F \rightarrow LiF + LiCl + 2Be + (3/2)O_2$
[167]	chlorination & fluorination	$2Li + 2Be + 2ClO_3F \rightarrow Be + BeF_2 + 2LiCl + 3O_2$
[168]	chlorination & fluorination	$4Li + 4Be + 6ClO_3F \rightarrow 3BeF_2 + 4LiCl + BeCl_2(g) + 9O_2$
[169]	chlorination & fluorination & oxygenation	$8Li + 8Be + 3ClO_3F \rightarrow 8BeO + Li_2O + 3LiF + 3LiCl$

Table 8. Calculated Phase Compatibilities in System Li-C-F at 1100 K

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[170]	Li-C-F	$10Li(\ell) + 2CF_4(g) \rightarrow Li_2C_2(c) + 8LiF(c)$	-620.7
[171]	Li-C-F	$4LiF(c) + 5C(c) \rightarrow 2Li_2C_2(c) + CF_4(g)$	+284.5
[172]	Li-C-F	$Li_2C_2(c) + 5F_2(g) \rightarrow 2CF_4(g) + 2LiF(c)$	-600.0
[173]	Li-C-F	$2C(c) + 2LiF(c) \rightarrow Li_2C_2(c) + 2F(g)$	+233.8
[174]	Li-C-F	$Li_2C_2(c) + 8F(g) \rightarrow 2Li(\ell) + 2CF_4(g)$	-355.9
[175]	Li-C-F	$4LiF(c) + C(g) \rightarrow 4Li(\ell) + CF_4(g)$	+305.2

Table 9. Calculated Phase Compatibilities in System Li-B-N-F at 1100 K

Reaction #	Subsystem	Reaction	ΔG_R (1100 K), kcal
[177]	Li-B-LiF-BF$_3$	$4Li(\ell) + BF_3(g) \rightarrow 3LiF(c) + LiB(c)$	-112.0
[178]	Li-B-LiF-BF$_3$	$3LiF(c) + B(c) \rightarrow 3Li(\ell) + BF_3(g)$	+110.5
[179]	Li-B-LiF-BF$_3$	$3LiF(c) + 3B(c) \rightarrow 3LiB(c) + BF_3(g)$	+106.0
[180]	Li-B-Li$_3$N-BN	$Li_3N(c) + LiB(c) \rightarrow 4Li(\ell) + BN(c)$	- 31.0
[181]	Li-B-Li$_3$N-BN	$Li_3N(c) + B(c) \rightarrow 3Li(\ell) + BN(c)$	- 32.5
[182]	Li-B-Li$_3$N-BN	$3LiB(c) + BN(c) \rightarrow Li_3N(c) + 4B(c)$	+ 37.1
[183]	Li$_3$N-BN-LiF-BF$_3$	$3LiF(c) + BN(c) \rightarrow Li_3N(c) + BF_3(g)$	+143.0

Table 10. Progressive Oxidation of LiB by NF_3

Reaction #	Reaction
[184]	$3LiB + NF_3 \rightarrow 2B + 3LiF + BN$
[185]	$3LiB + 2NF_3 \rightarrow 3LiF + BF_3 + 2BN$

Table 11. Comparison of Selected Liquid Metal Stored Chemical Energy Reactions

Reaction #	Primary Fuel	1st Stage Oxidant	1st Stage Reaction Products	2nd Stage Oxidant	2nd Stage Reaction Products	Total Calculated Enthalpy Yield at 1100 K in kcal/g (fuel & oxidant)*
[14]	Li	H_2O	Li_2O, H_2	O_2	H_2O	4.8
[169]	Li + Be	ClO_3F	BeO, Li_2O, LiF, LiCl	–	–	4.6
[186]	2Li + LiB	NF_3	LiF, BN	–	–	4.6
[2]	LiAl	H_2O	$LiAlO_2$, H_2	O_2	H_2O	4.3
[188]	Al	H_2O	Al_2O_3, H_2	O_2	H_2O	4.0
[21]	MgAl	H_2O	MgO, $MgAl_2O_4$, H_2	O_2	H_2O	3.8
[74x]	LiAl	ClO_3F	Al_2O_3, LiF, LiCl	–	–	3.8
[187]	Mg	H_2O	MgO, H_2	O_2	H_2O	3.6
[134]	LiAlMg	ClO_3F	MgF_2, LiF, LiCl, $MgAl_2O_4$, MgO	–	–	3.6
[13]	Li	H_2O	LiOH, H_2	O_2	H_2O	3.5
[176]	Li	$C_{11}F_{20}$	C, LiF	–	–	3.1**
[1]	Li	SF_6	LiF, Li_2S	–	–	3.0***
[20]	Li	H_2O	LiOH, H_2	$2NaO_2 + H_2\rightarrow$ $2NaOH(3/2)O_2$	H_2O	2.4

* Calculation ignores weight of recycled water in dual stage reactions

** Calculated at 298 K

*** From ref. (11)

XV. Figures

Figure 1. Thermogravimetric analysis of reaction of powdered lithium metal with flowing water-saturated argon at 25 and 100 °C.

Figure 2. Thermogravimetric analysis of reaction of powdered sodium
superoxide with flowing water-saturated argon at 25 and
100 °C.

Figure 3.   Thermogravimetric analysis of reaction of powdered MgAl alloy
with flowing water-saturated argon at 650 °C.

Figure 4.   Thermogravimetric analysis of reaction of powdered LiAl alloy
            with ClO_3F.   (a) 350 °C; (b) 450 °C; (c) 550 °C; (d) 650 °C.


Figure 5. Quaternary reciprocal systems relevant to oxidation of LiAl alloy by ClO_3F.

Figure 6. Calculated phase compatibilities in ternary reciprocal sub-systems of the system Li-Al-Cl-O-F at 1100 K, 1 atm.

Figure 7.   Outline of 1100 K, 1 atm phase compatibilities relating to
            oxidation of LiAl alloy by ClO_3F.   (a) chlorination and oxy-
            genation; (b) fluorination and oxygenation; (c) fluorination
   and chlorination.

Figure 8.   Outline of 1100 K, 1 atm phase compatibilities among products
            of complete oxidation of LiAl alloy by ClO₃F.

Figure 9.   Quaternary reciprocal systems relevant to oxidation of
LiAlMg alloy by ClO₃F.

Figure 10. Calculated phase compatibilities in ternary reciprocal sub-
systems of the system Li-Al-Mg-Cl-O-F at 1100 K, 1 atm.

Figure 10, continued.

Figure 10, continued.

Figure 11. Outline of 1100 K, 1 atm phase compatibilities relating to oxidation of LiAlMg alloy by ClO₃F. (a) chlorination; (b) fluorination; (c) oxygenation.

MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

Figure 12. Outline of 1100 K, 1 atm phase compatibilities among products
of complete oxidation of LiAlMg alloy by ClO₃F. (a) chlorina-
tion and oxygenation; (b) fluorination and oxygenation;
(c) fluorination and chlorination

Figure 13. Quaternary reciprocal systems relevant to oxidation of Li/Be mixtures by ClO₃F.

Figure 14. Calculated phase compatibilities in ternary reciprocal sub-
systems of the system Li-Be-Cl-O-F at 1100 K, 1 atm.

Figure 15. Outline of 1100 K, 1 atm phase compatibilities relating to
oxidation of Li/Be mixtures by ClO_3F. (a) chlorination and
oxygenation; (b) fluorination and oxygenation; (c) fluorina-
tion and chlorination.

Figure 16. Outline of phase compatibilities among products of complete oxidation of Li/Be by ClO₃F at 1100 K, 1 atm.

Figure 17.   Calculated phase compatibilities in the system Li-C-F at 1100 K, 1 atm.

Figure 18. Quaternary reciprocal systems relevant to oxidation of LiB alloy by NF_3.

Figure 19. Calculated phase compatibilities in ternary reciprocal subsystems of the system Li-B-F-N at 1100 K, 1 atm.

Figure 20. Outline of phase compatibilities among products of complete oxidation of LiB by NF_3 at 1100 K, 1 atm.

DL/432/84/316

ONR REPORT DISTRIBUTION LIST

CLOSED, LIQUID METAL COMBUSTION

One copy except
as noted

Mr. M. Keith Ellingsworth   2
Mechanics Division
Office of Naval Research
800 N. Quincy Street
Arlington, VA. 22217

Defense Documentation Center
Building 5, Cameron Station   12
Alexandria, VA. 22314

Technical Information Division
Naval Research Laboratory   6
4555 Overlook Avenue SW
Washington, DC 20375

Dr. Jerry A. Smith
Chemistry Division
Office of Naval Research
800 N. Quincy Street
Arlington, VA. 22217

Dr. Albert D. Wood
Technology Programs
Office of Naval Research
800 N. Quincy St.
Arlington, VA. 22217

Dr. H.W. Carhart
Combustion & Fuels
Naval Research Laboratory
Washington, DC 20375

Professor Allen Fuhs
Department of Aeronautics
Naval Post Graduate School
Monterey, California 93943

Division Director
Engineering and Weapons
US Naval Academy
Annapolis, Maryland 21402

Mr. Francis J. Romano
Code 63R3
Naval Sea Systems Command
Washington, DC 20363

DL/432/84/316

One copy except
as noted

Mr. Robert Tompkins
Code 36621, Bldg 126T
Naval Underwater Systems Center
Newport, Rhode Island 02841

Mr. Maurice F. Murphy
Code R33, Room 4-1711
Naval Surface Weapons, White Oak
Silver Spring, Maryland 20910

Dr. Kurt Mueller
Code R10
Energetic Materials Division
Naval Surface Weapons Center, White Oak
Silver Spring, Maryland 20910

Dr. Lynn A. Parnell
Code 6341
Naval Ocean Systems Center
San Diego, California 92152

Dr. Earl Quandt, Jr.
Code 2704
David Taylor Naval Ship
Research and Development Center
Annapolis, MD 21402

Mr. Richard Bloomquist
Code 2752
David Taylor Naval Ship R&D Center
Annapolis, Maryland 21402

Dr. Lawrence P. Cook
High Temperature Processes Group
National Bureau of Standards
Washington, DC 20234

DL/432/84/316

One copy except
as noted

Professor A. Murty Kanury
Department of Mechanical Engineering
Oregon State University
Corvallis, Oregon   97331

Professor Irvin Glassman
Department of Mechanical & Aerospace Engineering
Engineering Quadrangle
Princeton University
Princeton, New York   08544

Professor Norman Chigier
Department of Mechanical Engineering
Carnegie-Mellon University
Pittsburgh, Pennsylvania 15213

Professor George Janz
Cogswell Laboratory, R306
Department of Chemistry
Rensselaer Polytechnic Institute
Troy, New York   12181

Dr. Leonard Leibowitz
Chemical Technology Division
Argonne National Laboratory
9700 South Case Avenue
Argonne, Illinois   60439

Professor John Tarbell
104 Fenske Laboratory
Pennsylvania State University
University Park, Pennsylvania   16801

Professor Thomas E. Daubert
104 Fenske Laboratory
Pennsylvania State University
University State Park, Pennsylvania   16801

Dr. J. Braunstein
Research Division
Oak Ridge Operations
Department E
Oak Ridge, Tennessee   37831

DL/432/84/316

One copy except
as noted

Mr. Norman D. Hubele
Fluidic Systems, MS 1301-RR
Garrett Pneumatic Systems Division
2801 East Washington St.
Phoenix, Arizona 85034

Dr. Hugh H. Darsie
Advanced Technology Group
Sunstrand Energy Systems
4747 Harrison Avenue
Rockford, Illinois 61101

Professor Gerard M. Faeth
Department of Aerospace Engineering
University of Michigan
Ann Arbor, Michigan 48109

Dr. Dan H. Kiely
Power & Energy Group
The Pennsylvania State University
Applied Research Laboratory
P.O. Box 30
State College, Pennsylvania 16801

Professor Darryl E. Metzger
Department of Mechanical &
Aerospace Engineering
Arizona State University
Tempe, Arizona 85281

Dr. Dae H. Cho
Reactor Analysis & Safety Division
Argonne National Laboratory
Argonne, Illinois 60439

Professor S.H. Chan
Department of Mechanical Engineering
The University of Wisconsin-Milwaukee
P.O. Box 784
Milwaukee, Wisconsin 53201

Professor George A. Brown
Department of Mechanical Engineering
and Applied Mechanics
University of Rhode Island
Kingston, Rhode Island 02881

4. TITLE AND SUBTITLE

Survey of Alternate Stored Chemical Energy Reactions

5. AUTHOR(S)

L.P. Cook and E.R. Plante

11. ABSTRACT (A 200-word or less factual summary of most significant information. If document includes a significant bibliography or literature survey, mention it here)

A survey of eight alternative liquid metal stored chemical energy reactions has been made for purposes of comparison with the lithium-aluminum/water, lithium/sulfur hexafluoride, and other reaction schemes. The objective of the study was to survey the potential of these eight reactions as alternate stored chemical energy systems and to develop priorities for future study. Experimental data on the products of reaction and kinetics of reaction are presented for: (Li/H_2O; H_2/O_2), (Li/H_2O; NaO_2/H_2O; H_2/O_2), ($MgAl/H_2O$; H_2/O_2), and ($LiAl/ClO_3F$). These data have been collected using thermogravimetry and Knudsen effusion mass spectrometry, with x-ray diffraction analysis of experimental products. Among other results, the data show that the aluminum component of the fuels is relatively inert to oxidation up to 650 $^{\circ}$C. Above this temperature, materials limitations have hampered the collection of experimental data.

Thermodynamic analysis has been used to extend the data on each of the eight reaction schemes, and to predict the chemical reaction with best represents the complete oxidation of each fuel by the indicated oxidant at 1100 K. Enthalpies have been calculated for each fuel/oxidant combination. Safety considerations are also discussed for each. Suggestions for future research are given, including suggestions for overcoming the materials problems encountered in this study.

12. KEY WORDS (Six to twelve entries; alphabetical order; capitalize only proper names; and separate key words by semicolons)

enthalpy yield, kinetics, liquid metal combustion, lithium, lithium-aluminum lithium -boron, lithium-beryllium, magnesium-alumium, nitrogen trifluoride, water

END

FILMED

2 4-86

DTIC